



Standard Specification for Pressure Vessel Plates, Alloy Steel, Higher Strength Chromium-Molybdenum-Tungsten¹

This standard is issued under the fixed designation A 1041/A 1041M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers chromium-tungsten-molybdenum-vanadium, with or without tantalum, alloy steel plates intended primarily for welded boilers and pressure vessels designed for elevated temperature service.

1.2 Plates are available under this specification in two grades having different alloy contents as follows:

Grade	Nominal Chromium Content, %	Nominal Tungsten Content, %	Nominal Molybdenum Content, %	Nominal Vanadium Content, %	Nominal Tantalum Content, %
315	3.00	1.50	0.75	0.25	
315T	3.00	1.50	0.75	0.25	0.10

1.3 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements.

1.4 The specification is expressed in both inch-pound units and in SI units; however, unless the order specifies the applicable “M” specification designation (SI units), the plates are furnished to inch-pound units.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved May 1, 2009. Published May 2009. Originally approved in 2004. Last previous edition approved in 2004 as A 1041/A 1041M – 04.

2. Referenced Documents

2.1 ASTM Standards:²

- A 20/A 20M Specification for General Requirements for Steel Plates for Pressure Vessels
- A 435/A 435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates
- A 577/A 577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates
- A 578/A 578M Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

3. General Requirements

3.1 Product furnished to this specification shall conform to Specification A 20/A 20M, including any supplementary requirements indicated in the purchase order or contract. Failure to comply with the general requirements of Specification A 20/A 20M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 20/A 20M, the requirements of this specification shall prevail.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available if additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A 20M.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.