



Designation: A335/A335M – 26

Standard Specification for Seamless Ferritic Alloy-Steel Pipe for High-Temperature Service¹

This standard is issued under the fixed designation A335/A335M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers nominal wall and minimum wall seamless ferritic alloy-steel pipe intended for high-temperature service. Pipe ordered to this specification shall be suitable for bending, flanging (vanstoning), and similar forming operations, and for fusion welding. Selection will depend upon design, service conditions, mechanical properties, and high-temperature characteristics.

1.2 Several grades of ferritic steels (see **Note 1**) are covered. Their compositions are given in **Table 1**.

NOTE 1—Ferritic steels in this specification are defined as low- and intermediate-alloy steels containing up to and including 10 % chromium.

1.3 Supplementary requirements (S1 to S9) of an optional nature are provided. Supplementary requirements S1 through S6 call for additional tests to be made, and when desired, shall be so stated in the order together with the number of such tests required as applicable.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

NOTE 2—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved April 1, 2026. Published April 2026. Originally approved in 1951. Last previous edition approved in 2024 as A335/A335M – 24b. DOI: 10.1520/A0335_A0335M-26.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-335 in Section II of that Code.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

A999/A999M Specification for General Requirements for Alloy and Stainless Steel Pipe

E92 Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials

E213 Practice for Ultrasonic Testing of Metal Pipe and Tubing

E309 Practice for Eddy Current Examination of Steel Tubular Products

E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

E570 Practice for Flux Leakage Examination of Ferromagnetic Steel Tubular Products

2.2 ASME Standard:

B36.10M Welded and Seamless Wrought Steel Pipe

2.3 AWS Specifications⁴

A5.5/A5.5M Specification for Low-Alloy Steel Electrodes for Shielded Metal Arc Welding

A5.23/A5.23M Specification for Low-Alloy Steel Electrodes and Fluxes for Submerged Arc Welding

A5.28/A5.28M Specification for Low-Alloy Steel Electrodes for Gas Shielded Arc Welding

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.

*A Summary of Changes section appears at the end of this standard



TABLE 1 Chemical Requirements

Grade	UNS Designation ^A	Composition, %							
		Carbon	Manganese	Phosphorus, max	Sulfur, max	Silicon	Chromium	Molybdenum	Others
P1	K11522	0.10–0.20	0.30–0.80	0.025	0.025	0.10–0.50	...	0.44–0.65	...
P2	K11547	0.10–0.20	0.30–0.61	0.025	0.025	0.10–0.30	0.50–0.81	0.44–0.65	...
P5	K41545	0.15 max	0.30–0.60	0.025	0.025	0.50 max	4.00–6.00	0.45–0.65	...
P5b	K51545	0.15 max	0.30–0.60	0.025	0.025	1.00–2.00	4.00–6.00	0.45–0.65	...
P5c	K41245	0.12 max	0.30–0.60	0.025	0.025	0.50 max	4.00–6.00	0.45–0.65	... ^B
P9	K90941	0.15 max	0.30–0.60	0.025	0.025	0.25–1.00	8.00–10.00	0.90–1.10	...
P11	K11597	0.05–0.15	0.30–0.60	0.025	0.025	0.50–1.00	1.00–1.50	0.44–0.65	...
P12	K11562	0.05–0.15	0.30–0.61	0.025	0.025	0.50 max	0.80–1.25	0.44–0.65	...
P15	K11578	0.05–0.15	0.30–0.60	0.025	0.025	1.15–1.65	...	0.44–0.65	...
P21	K31545	0.05–0.15	0.30–0.60	0.025	0.025	0.50 max	2.65–3.35	0.80–1.06	...
P22	K21590	0.05–0.15	0.30–0.60	0.025	0.025	0.50 max	1.90–2.60	0.87–1.13	...
P23	K40712	0.04–0.10	0.10–0.60	0.030 max	0.010 max	0.50 max	1.90–2.60	0.05–0.30	V 0.20–0.30 Nb ^F 0.02–0.08 B 0.0010–0.006 N 0.015 max Al 0.030 max W 1.45–1.75 Ni 0.40 max Ti 0.005–0.060 Ti/N ≥ 3.5 ^C
P24	K30736	0.05–0.10	0.30–0.70	0.020	0.010	0.15–0.45	2.20–2.60	0.90–1.10	V 0.20–0.30 Ti 0.06–0.10 N 0.012 max Al 0.02 max B 0.0015–0.007 Ni 1.00–1.30 Cu 0.50–0.80 Nb ^F 0.015–0.045 V 0.02 max N 0.02 max Al 0.050 max
P36	K21001	0.10–0.17	0.80–1.20	0.030 max	0.025 max	0.25–0.50	0.30 max	0.25–0.50	V 0.18–0.25 N 0.030–0.070 Ni 0.40 max Al 0.02 max Nb ^F 0.06–0.10 Ti 0.01 max Zr 0.01 max
P91 Type 1	K90901	0.08–0.12	0.30–0.60	0.020	0.010	0.20–0.50	8.00–9.50	0.85–1.05	V 0.18–0.25 N 0.030–0.070 Ni 0.40 max Al 0.02 max Nb ^F 0.06–0.10 Ti 0.01 max Zr 0.01 max
P91 Type 2 Heat Product	K90901	0.08–0.12 0.07–0.13	0.30–0.50 ^D	0.020 ^D	0.005 ^D	0.20–0.40 ^D	8.00–9.50 ^D	0.85–1.05 0.80–1.05	V Heat 0.18–0.25 Product 0.16–0.27 Ni 0.20 max ^D Al 0.020 max ^D N 0.035–0.070 ^D N/Al ratio ≥ 4.0 Nb ^F Heat 0.06–0.10 Product 0.05–0.11 Ti 0.01 max ^D Zr 0.01 max ^D Sn 0.010 max ^D Sb 0.003 max ^D As 0.010 max ^D B 0.001 max ^D W 0.05 max ^D Cu 0.10 max ^D
P92	K92460	0.07–0.13	0.30–0.60	0.020	0.010	0.50 max	8.50–9.50	0.30–0.60	V 0.15–0.25 N 0.03–0.07 Ni 0.40 max Al 0.02 max Nb ^F 0.04–0.09 W 1.5–2.00 B 0.001–0.006 Ti 0.01 max Zr 0.01 max