



Designation: A576 – 23

Standard Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality¹

This standard is issued under the fixed designation A576; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers hot-wrought special quality carbon steel bars. Special quality bar applications include forging, heat treating, cold drawing, machining, and many structural uses. A guide for the selection of steel bars is contained in Practice A400.

1.2 The bars shall be furnished in the grades specified in Table 1. Sections and sizes of bar steel available are covered in Specification A29/A29M. Hot-wrought special quality carbon steel bars are produced in cut lengths and coils; the manufacturer should be consulted regarding sections and sizes available in coils, produced to a chemical composition.

1.3 Merchant quality hot-wrought carbon steel bars are covered in Specification A575.

1.4 Some end uses may require superior surface quality, or special chemical restrictions, metallurgical characteristics, heat treatment, or surface finishes which the purchaser may obtain by designating one or more of the available Supplementary Requirements.

1.5 The values stated in inch-pound units are to be regarded as standard.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.15 on Bars.

Current edition approved Nov. 1, 2023. Published November 2023. Originally approved in 1967. Last previous edition approved in 2017 as A576 – 17. DOI: 10.1520/A0576-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

A29/A29M Specification for General Requirements for Steel Bars, Carbon and Alloy, Hot-Wrought

A400 Practice for Steel Bars, Selection Guide, Composition, and Mechanical Properties

A575 Specification for Steel Bars, Carbon, Merchant Quality, M-Grades

A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

E45 Test Methods for Determining the Inclusion Content of Steel

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 SAE Standard:

SAE J 1086 Recommended Practice for Numbering Metals and Alloys (UNS)³

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this standard, refer to Terminology A941.

4. Ordering Information

4.1 Orders under this specification should include the following, as required, to describe adequately the desired material:

4.1.1 Quantity (weight or number of bars),

4.1.2 Name of material (hot-wrought carbon steel bars),

4.1.3 Dimensions,

4.1.4 ASTM specification number and date of issue,

4.1.5 Deoxidation practice (see 5.2.1),

4.1.6 Grade designation or chemical composition limits (see 6.1 and Table 1),

4.1.7 Coarse or fine grain steel (5.2.2),

4.1.8 Test reports, if required (Section 8),

4.1.9 Additions to the specification and Supplementary Requirements, if required, and

4.1.10 End use.

³ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Grade Designations and Chemical Requirements of Hot-Wrought Carbon Steel Bars

NOTE 1—Grade designations and compositions correspond to the respective SAE designations and compositions.

UNS Designation ^A	Grade	Heat Chemical Ranges and Limits, %			
		Carbon	Manganese	Phosphorus, max	Sulfur, max ^B
		Nonresulfurized Carbon Steels ^{C, D, E, F, G}			
Low Manganese 1.00 % max or less					
G10080	1008	0.10 max	0.30–0.50	0.040	0.050
G10100	1010	0.08–0.13	0.30–0.60	0.040	0.050
G10120	1012	0.10–0.15	0.30–0.60	0.040	0.050
G10150	1015	0.13–0.18	0.30–0.60	0.040	0.050
G10160	1016	0.13–0.18	0.60–0.90	0.040	0.050
G10170	1017	0.15–0.20	0.30–0.60	0.040	0.050
G10180	1018	0.15–0.20	0.60–0.90	0.040	0.050
G10190	1019	0.15–0.20	0.70–1.00	0.040	0.050
G10200	1020	0.18–0.23	0.30–0.60	0.040	0.050
G10210	1021	0.18–0.23	0.60–0.90	0.040	0.050
G10220	1022	0.18–0.23	0.70–1.00	0.040	0.050
G10230	1023	0.20–0.25	0.30–0.60	0.040	0.050
G10250	1025	0.22–0.28	0.30–0.60	0.040	0.050
G10260	1026	0.22–0.28	0.60–0.90	0.040	0.050
G10290	1029	0.25–0.31	0.60–0.90	0.040	0.050
G10300	1030	0.28–0.34	0.60–0.90	0.040	0.050
G10350	1035	0.32–0.38	0.60–0.90	0.040	0.050
G10370	1037	0.32–0.38	0.70–1.00	0.040	0.050
G10380	1038	0.35–0.42	0.60–0.90	0.040	0.050
G10390	1039	0.37–0.44	0.70–1.00	0.040	0.050
G10400	1040	0.37–0.44	0.60–0.90	0.040	0.050
G10420	1042	0.40–0.47	0.60–0.90	0.040	0.050
G10430	1043	0.40–0.47	0.70–1.00	0.040	0.050
G10440	1044	0.43–0.50	0.30–0.60	0.040	0.050
G10450	1045	0.43–0.50	0.60–0.90	0.040	0.050
G10460	1046	0.43–0.50	0.70–1.00	0.040	0.050
G10490	1049	0.46–0.53	0.60–0.90	0.040	0.050
G10500	1050	0.48–0.55	0.60–0.90	0.040	0.050
G10530	1053	0.48–0.55	0.70–1.00	0.040	0.050
G10550	1055	0.50–0.60	0.60–0.90	0.040	0.050
G10600	1060	0.55–0.65	0.60–0.90	0.040	0.050
G10700	1070	0.65–0.75	0.60–0.90	0.040	0.050
G10780	1078	0.72–0.85	0.30–0.60	0.040	0.050
G10800	1080	0.75–0.88	0.60–0.90	0.040	0.050
G10840	1084	0.80–0.93	0.60–0.90	0.040	0.050
G10900	1090	0.85–0.98	0.60–0.90	0.040	0.050
G10950	1095	0.90–1.03	0.30–0.50	0.040	0.050
High Manganese 1.65 % max or less					
G15130	1513	0.10–0.16	1.10–1.40	0.040	0.050
G15180	1518	0.15–0.21	1.10–1.40	0.040	0.050
G15220	1522	0.18–0.24	1.10–1.40	0.040	0.050
G15240	1524	0.19–0.25	1.35–1.65	0.040	0.050
G15250	1525	0.23–0.29	0.80–1.10	0.040	0.050
G15260	1526	0.22–0.29	1.10–1.40	0.040	0.050
G15270	1527	0.22–0.29	1.20–1.50	0.040	0.050
G15360	1536	0.30–0.37	1.20–1.50	0.040	0.050
G15410	1541	0.36–0.44	1.35–1.65	0.040	0.050
G15470	1547	0.43–0.51	1.35–1.65	0.040	0.050
G15480	1548	0.44–0.52	1.10–1.40	0.040	0.050
G15510	1551	0.45–0.56	0.85–1.15	0.040	0.050
G15520	1552	0.47–0.55	1.20–1.50	0.040	0.050
G15610	1561	0.55–0.65	0.75–1.05	0.040	0.050
G15660	1566	0.60–0.71	0.85–1.15	0.040	0.050
G15720	1572	0.65–0.76	1.00–1.30	0.040	0.050
Resulfurized Carbon Steels ^{C, E, G}					
G11090	1109	0.08–0.13	0.60–0.90	0.040	0.08–0.13
G11100	1110	0.08–0.13	0.30–0.60	0.040	0.08–0.13
G11160	1116	0.14–0.20	1.10–1.40	0.040	0.16–0.23
G11170	1117	0.14–0.20	1.00–1.30	0.040	0.08–0.13
G11180	1118	0.14–0.20	1.30–1.60	0.040	0.08–0.13
G11190	1119	0.14–0.20	1.00–1.30	0.040	0.24–0.33
G11320	1132	0.27–0.34	1.35–1.65	0.040	0.08–0.13
G11370	1137	0.32–0.39	1.35–1.65	0.040	0.08–0.13
G11390	1139	0.35–0.43	1.35–1.65	0.040	0.13–0.20
G11400	1140	0.37–0.44	0.70–1.00	0.040	0.08–0.13
G11410	1141	0.37–0.45	1.35–1.65	0.040	0.08–0.13
G11440	1144	0.40–0.48	1.35–1.65	0.040	0.24–0.33
G11450	1145	0.42–0.49	0.70–1.00	0.040	0.04–0.07
G11460	1146	0.42–0.49	0.70–1.00	0.040	0.08–0.13
G11510	1151	0.48–0.55	0.70–1.00	0.040	0.08–0.13