



Designation: A757/A757M – 22

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing and Other Applications, for Low-Temperature Service¹

This standard is issued under the fixed designation A757/A757M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers carbon and alloy steel castings for pressure-containing and other applications intended primarily for petroleum and gas pipelines in areas subject to low-ambient temperatures. Castings shall be heat treated by normalizing and tempering or liquid quenching and tempering. All classes are weldable under proper conditions. Hardenability of some grades may limit usable section size.

1.2 The values stated in either inch-pound units or SI units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.2.1 Unless the order specifies an “M” designation, the material shall be furnished to inch-pound units.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Nov. 1, 2022. Published December 2022. Originally approved in 1978. Last previous edition approved in 2015 as A757/A757M – 15. DOI: 10.1520/A0757_A0757M-22.

2. Referenced Documents

2.1 ASTM Standards:²

A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel

A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts

A985/A985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts

A1067/A1067M Specification for Test Coupons for Steel Castings

2.2 American Society of Mechanical Engineers:³

ASME Boiler and Pressure Vessel Code

2.3 Manufacturers Standardization Society of the Valve and Fittings Industry Standards:⁴

MSS SP-55 Quality Standard for Steel Castings for Valves, Flanges, Fittings, and Other Piping Components—Visual Method for Evaluation of Surface Irregularities

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *nominal thickness, T, n*—for quenched and tempered castings with a thickness exceeding 2 in. [50 mm], the maximum thickness of the pressure-containing wall of the casting exclusive of padding added for directional solidification, flanges, appendages, and sections designated by the designer as noncritical.

4. General Conditions for Delivery

4.1 Except for investment castings, castings furnished to this specification shall be in accordance with the requirements

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁴ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Composition Requirements^{A,B}

Element, %	Grade ^C Type									
	A1Q C	A2Q C-Mn	B2N, B2Q 2.5Ni	B3N, B3Q 3.5Ni	B4N, B4Q 4.5Ni	C1Q Ni-Mo	D1N, D1Q Cr-Mo	E1Q Ni-Cr-Mo	E2N, E2Q Ni-Cr-Mo	E3N Martensitic Cr-Ni
Carbon	0.30	0.25 ^D	0.25	0.15	0.15	0.25	0.20	0.22	0.20	0.06
Manganese	1.00	1.20 ^D	0.50–0.80	0.50–0.80	0.50–0.80	1.20	0.40–0.80	0.50–0.80	0.40–0.70	1.00
Phosphorus	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^F	0.020 ^F	0.030 ^G
Sulfur	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^E	0.025 ^F	0.020 ^F	0.030 ^G
Silicon	0.60	0.60	0.60	0.60	0.60	0.60	0.60	0.60	0.60	1.00
Nickel	0.50 ^E	0.50 ^E	2.0–3.0	3.0–4.0	4.0–5.0	1.5–2.0	0.50 ^E	2.5–3.5	2.75–3.90	3.5–4.5
Chromium	0.40 ^E	0.40 ^E	0.40 ^E	0.40 ^E	0.40 ^E	0.40 ^E	2.0–2.75	1.35–1.85	1.50–2.0	11.5–14.0
Molybdenum	0.25 ^E	0.25 ^E	0.25 ^E	0.25 ^E	0.25 ^E	0.15–0.30	0.90–1.20	0.35–0.60	0.40–0.60	0.40–1.0
Copper	0.50 ^E	0.50 ^E	0.50 ^E	0.50 ^E	0.50 ^E	0.50 ^E	0.50 ^E	0.50 ^F	0.50 ^F	0.50 ^G
Vanadium	0.03 ^E	0.03 ^E	0.03 ^E	0.03 ^E	0.03 ^E	0.03 ^E	0.03 ^E	0.03 ^F	0.03 ^F	...
Tungsten	...	...	...	...	...	...	0.10 ^E	...	0.10 ^F	0.10 ^G

^A All values are maximums unless a range is provided.

^B Where ellipses (. . .) appear in this table, there is no requirement and the element need not be analyzed for or reported.

^C "Q" in the grade name indicates that the casting has been quenched and tempered. "N" in the grade name indicates that the casting has been normalized and tempered.

^D For each 0.01 % of reduction in carbon below the maximum specified, an increase of 0.04 % manganese over the maximum specified will be permitted up to 1.40 %.

^E The total content of these elements shall not exceed 1.00 % including phosphorus and sulfur.

^F The total content of these elements shall not exceed 0.70 % including phosphorus and sulfur.

^G The total content of these elements shall not exceed 0.50 % including phosphorus and sulfur.

of Specification **A703/A703M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A703/A703M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A703/A703M**, this specification shall prevail.

4.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification **A985/A985M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A985/A985M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A985/A985M**, **A985/A985M** shall prevail.

5. Ordering Information

5.1 Orders for material to this specification should include the following, as required, to describe the material adequately:

- 5.1.1 Quantity,
- 5.1.2 ASTM designation and date of issue,
- 5.1.3 Grade designation,
- 5.1.4 Class (if applicable),
- 5.1.5 Description of casting by part, pattern, or drawing number (dimensional tolerances and machined surfaces should be indicated on the casting drawing),
- 5.1.6 Options in the specification,
- 5.1.7 Whether the castings are to be produced using investment casting process, and
- 5.1.8 Supplementary requirements desired, if any, including standards of acceptance.

6. Materials and Manufacture

6.1 *Melting Process*—The steel shall be made by the electric furnace process or other primary processes approved by the

purchaser. The primary melting may incorporate separate degassing or refining and may be followed by secondary melting.

6.2 Heat Treatment:

6.2.1 All castings shall be heat treated by either normalizing and tempering or quenching and tempering. Tempering temperature shall be 1100 °F [595 °C] minimum, except grades B4N and B4Q, which shall be tempered at 1050 °F [565 °C] minimum.

6.2.2 E3N castings shall be heat treated by heating to 1850 °F [1010 °C] minimum, and air cooling to 200 °F [95 °C] or cooler before any optional intermediate temper, but shall be cooled to 100 °F [40 °C] or cooler before the final temper, which shall be between 1050 and 1150 °F [565 and 620 °C].

6.2.3 Furnace temperatures for heat treating shall be controlled by thermocouples.

6.2.4 Castings shall be allowed to cool below the transformation range directly after pouring and solidification before they are reheated for normalizing or liquid quenching.

7. Chemical Composition

7.1 The steel shall be in accordance with the requirements as to chemical composition prescribed in **Table 1**.

8. Tensile Requirements

8.1 Steel used for the castings shall conform to the requirements as to the tensile properties prescribed in **Table 2**.

9. Impact Requirements

9.1 Impact properties shall be determined on each heat by testing a set of three Charpy V-notch specimens. The bar from which the impact specimens are machined shall be prepared in accordance with Section 12. The longitudinal axis of the Charpy specimens shall be parallel to the longitudinal axis of the tensile bar.