



Designation: B704 – 23

Standard Specification for Welded Nickel Alloy Tubes¹

This standard is issued under the fixed designation B704; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers welded UNS N06219, UNS N06625, UNS N08642, UNS N08825, and UNS N08827 nickel alloy boiler, heat exchanger, and condenser tubes for general corrosion resisting and low or high-temperature service.

1.2 This specification covers tubes 1/8 in. to 5 in. (3.18 mm to 127 mm), inclusive, in outside diameter and 0.015 in. to 0.500 in. (0.38 mm to 12.70 mm), inclusive, in wall thickness. Specification B751 lists the dimensional requirements of these sizes. Tubes having other dimensions may be furnished provided such tubing complies with all other requirements of this specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2023. Published November 2023. Originally approved in 1982. Last previous edition approved in 2019 as B704 – 19. DOI: 10.1520/B0704-23.

2. Referenced Documents

2.1 *ASTM Standards:*²

B751 Specification for General Requirements for Nickel and Nickel Alloy Welded Tube

B899 Terminology Relating to Non-ferrous Metals and Alloys

E8/E8M Test Methods for Tension Testing of Metallic Materials

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology B899.

4. Ordering Information

4.1 Orders for material to this specification should include the following information:

4.1.1 Quantity (feet or number of lengths),

4.1.2 UNS number,

4.1.3 Size (outside diameter, minimum or average wall thickness),

4.1.4 Length (random or specific),

4.1.5 Class, and

4.1.6 Grade if UNS N06625 is specified. If neither grade of N06625 is specified, grade 1 will be supplied.

4.1.7 ASTM designation.

4.1.8 *Product Analysis*—State if required.

4.1.9 *Purchaser Inspection*—State which tests or inspections are to be witnessed, if any.

5. Materials and Manufacture

5.1 Tube shall be made from flat-rolled alloy by an automatic welding process with no addition or filler metal. Subsequent to welding and prior to final annealing, the material shall be cold-worked in either the weld metal only or both weld and base metal.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard