



Designation: B869 – 07 (Reapproved 2023)

Standard Specification for Copper-Clad Steel Electrical Conductor for CATV Drop Wire¹

This standard is issued under the fixed designation B869; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers 21 % conductivity hard-drawn round copper-clad steel wire for coaxial cable center conductors (**Note 1**).

NOTE 1—Wire ordered to this specification is not intended for redrawing since it is furnished in the hard-drawn temper. If wire is desired for the purpose, the manufacturer should be consulted.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents, of the issue in effect on the date of material purchase, form a part of this specification to the extent referenced herein.

2.2 *ASTM Standards:*²

B193 Test Method for Resistivity of Electrical Conductor Materials

B258 Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors

2.3 *NIST Document:*³

NBS Handbook 100—Copper Wire Tables

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.06 on Bi-Metallic Conductors.

Current edition approved Oct. 1, 2023. Published October 2023. Originally approved in 1996. Last previous edition approved in 2018 as B869 – 07 (2018). DOI: 10.1520/B0869-07R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size;

3.1.2 Wire size: diameter in inches (see 5.1 and Table 1);

3.1.3 Package size (see 15.1);

3.1.4 Special package marking, if required (Section 15); and

3.1.5 Place of inspection (13.2).

4. Material

4.1 The wire shall be composed of a steel core with a substantially uniform and continuous copper cladding thoroughly bonded to it throughout.

4.2 The finished copper-clad steel wire shall conform to the requirements in this specification.

5. Dimensions and Permissible Variations

5.1 The size shall be expressed as the diameter of the wire in decimal fractions of an inch, using four places of decimals, that is, in tenths of a mil (**Note 2**).

NOTE 2—The values of wire diameters in Table 1 and Table 2 are given to the nearest 0.0001 in. (0.0025 mm) and correspond to the standard sizes given in Specification B258. In specifying diameters of wire or inspecting wire, the diameter should also be expressed to the fourth decimal place. An excellent discussion of wire gauges and related subjects is contained in *NBS Handbook 100*.

5.2 Within the range of diameters included in Table 1, the wire shall not vary from the specified diameter by more than ± 1 %, expressed to the nearest 0.0001 in. (0.0025 mm).

5.3 Ten percent, but not less than five reels (or all, if the lot is less than five), from any lot of wire shall be gauged. All reels shall be gauged if any of the selected reels fail to conform to the requirements for diameter.

6. Workmanship, Finish, and Appearance

6.1 The surface of the wire shall be free from imperfections and be consistent with good commercial practice.

7. Tensile and Elongation Properties

7.1 The wire shall conform to a minimum tensile requirement of 120 000 psi (827 MPa) and a minimum elongation requirement of 1.0 %.