



Standard Specification for Chemical-Resistant Carbon Brick¹

This standard is issued under the fixed designation C1160; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers machine made solid uncured carbon brick produced from either metallurgical or petroleum calcined coke, baked to a minimum 1850°F (1010°C), and suitable for use in masonry construction which will be exposed to various chemicals. These units are designed primarily for industries using hydrofluoric acid, fluoride salts, and high concentrations of alkalis such as sodium and potassium hydroxide. Carbon brick are normally used with carbon filled chemical-resistant mortars.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C67 Test Methods for Sampling and Testing Brick and Structural Clay Tile
- C561 Test Method for Ash in a Graphite Sample
- C904 Terminology Relating to Chemical-Resistant Nonmetallic Materials
- C1106 Test Methods for Chemical Resistance and Physical Properties of Carbon Brick

3. Terminology

3.1 **Definitions**—For definitions of terms used in this specification, see Terminology C904.

¹ This specification is under the jurisdiction of ASTM Committee C03 on Chemical-Resistant Nonmetallic Materials and is the direct responsibility of Subcommittee C03.02 on Monolithics, Grouts and Polymer Concretes.

Current edition approved Aug. 1, 2012. Published September 2012. Originally approved in 1990. Last previous edition approved in 2008 as C1160 – 97 (2008). DOI: 10.1520/C1160-97R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 The chemical-resistant carbon brick meeting this specification is intended for use in acid and alkaline service at varying temperatures. Physical stress imposed on the brick attributable to thermal shock or pressure differential may or may not be a consideration. The corrosion resistance and structural integrity of the brick are dependent on the type and purity of the carbon and binder used when the brick is manufactured.

4.2 The performance of the brick as tested in Test Methods C1106 or other tests, or other qualifying data, should be reviewed between the purchaser and the seller.

5. Sampling

5.1 The brick shall be sampled in accordance with Test Methods C67.

6. Chemical Resistance

6.1 Carbon brick are inherently non-wetting and highly resistant to many acids, alkalis, salts, and solvents and combinations of these chemicals at varying temperatures and concentrations.

6.2 The carbon brick shall be tested in accordance with Test Methods C1106 using a chemical and thermal environment.

6.3 To comply with this specification, the carbon brick shall exhibit chemical resistance to those chemical media stated in Table 1 when carried out at ambient temperature in accordance with Test Methods C1106.

7. Physical Properties

7.1 The carbon brick shall comply with the values shown in Table 2 for compressive strength, modulus of rupture, and water absorption when tested according to Test Methods C1106.

7.2 The carbon brick shall have a maximum ash content of 8% when tested in accordance with Test Method C561.

8. Sizes

8.1 The sizes and tolerances of brick shall be as specified by the purchaser. The measurement of sizes shall be in accordance with Test Method C67, with the maximum permissible variation in dimensions of individual units not exceeding those in Table 3.