



Designation: C1505 – 15 (Reapproved 2022)

# Standard Test Method for Determination of Breaking Strength and Modulus of Rupture of Ceramic Tiles and Glass Tiles by Three-Point Loading<sup>1</sup>

This standard is issued under the fixed designation C1505; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of breaking strength and modulus of rupture of ceramic tiles and glass tiles by three-point loading.

1.2 *Units*—The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C242 Terminology of Ceramic Whitewares and Related Products

## 3. Terminology

3.1 For the definitions of terms used on this test method, refer to Terminology C242.

## 4. Summary of Test Method

4.1 This test method consists of determining the breaking strength and modulus of rupture of ceramic tiles and glass tiles

using a three-point loading method. The tiles are supported on two cylindrical support rods positioned to provide an appropriate span. A load is applied at a uniform rate using a third central cylindrical rod positioned at the midpoint between the support rods. The breaking strength and modulus of rupture are calculated using the load at which tile failure is observed, the dimensions of the tile specimen, and the span between the support rods. Optionally, the deflection at which the tile failure is observed may be reported.

## 5. Significance and Use

5.1 This test method is intended for determining the breaking strength and modulus of rupture of ceramic tiles and glass tiles for compliance with requirements that may appear in specifications.

## 6. Apparatus

6.1 *Testing Machine*, capable of loading at a uniform rate sufficient to increase the stress in the specimen at a rate of  $1 \pm 0.2 \text{ N/mm}^2$  ( $145 \pm 29 \text{ psi}$ ) per second. At minimum, the testing machine shall record loading data at the point at which specimen failure is observed. Optionally, the testing machine may record deflection data. The rod support table of the testing machine shall be adjustable such that the cylindrical support rods can accommodate a variety of specimen sizes.

6.2 *Cylindrical Support Rods*, 2, of length,  $w$ , with a steel core of diameter,  $d$ , and a rubber bearing surface of  $55 \pm 3$  Shore A durometer hardness and thickness,  $t$  (see Table 1). One rod shall be permitted to pivot slightly relative to its length and the other shall be permitted to rotate slightly relative to its axis (see Fig. 1).

6.3 *Central Cylindrical Rod*, of length,  $w$ , with a steel core of diameter,  $d$ , and a rubber bearing surface of  $55 \pm 3$  Shore A durometer hardness and thickness,  $t$ . The rod shall be permitted to pivot slightly relative to its axis.

## 7. Sampling

7.1 The test sample shall consist of ten whole tiles, selected at random from the lot to be tested. Tiles too large to be tested whole may be cut; however, the cut specimens shall be square and as large as possible, though not larger than the rod length.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved Feb. 1, 2022. Published March 2022. Originally approved in 2001. Last previous edition approved in 2015 as C1505 – 15. DOI: 10.1520/C1505-15R22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.