



Designation: C887 – 20

Standard Specification for Packaged, Dry, Combined Materials for Surface Bonding Mortar¹

This standard is issued under the fixed designation C887; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the materials, properties, and packaging of dry, combined materials for use as surface bonding mortar with concrete masonry units that have not been prefaced, coated, or painted.

1.2 This specification does not cover design or application. Consult the manufacturer for specific recommendations.

1.3 **Appendix X1** of this specification contains the recommended tests for evaluation of surface bonded masonry assemblages used to establish design loads for the composite wall.

1.4 **Appendix X2** through **Appendix X5** of this specification contain additional tests that may be performed on surface bonding mortar.

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. This hazard statement applies only to Section 9 of this specification.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.06 on Surface Bonding.

Current edition approved June 15, 2020. Published July 2020. Originally approved in 1979. Last previous edition approved in 2019 as C887 – 19a. DOI: 10.1520/C0887-20.

2. Referenced Documents

2.1 *ASTM Standards:*²

- C91/C91M Specification for Masonry Cement
- C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50 mm] Cube Specimens)
- C138/C138M Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete
- C144 Specification for Aggregate for Masonry Mortar
- C150/C150M Specification for Portland Cement
- C187 Test Method for Amount of Water Required for Normal Consistency of Hydraulic Cement Paste
- C191 Test Methods for Time of Setting of Hydraulic Cement by Vicat Needle
- C207 Specification for Hydrated Lime for Masonry Purposes
- C260/C260M Specification for Air-Entraining Admixtures for Concrete
- C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency
- C348 Test Method for Flexural Strength of Hydraulic-Cement Mortars
- C349 Test Method for Compressive Strength of Hydraulic-Cement Mortars (Using Portions of Prisms Broken in Flexure)
- C359 Test Method for Early Stiffening of Hydraulic Cement (Mortar Method)
- C494/C494M Specification for Chemical Admixtures for Concrete
- C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes
- C595/C595M Specification for Blended Hydraulic Cements

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C666/C666M Test Method for Resistance of Concrete to Rapid Freezing and Thawing
- C1157/C1157M Performance Specification for Hydraulic Cement
- C1180 Terminology of Mortar and Grout for Unit Masonry
- C1232 Terminology for Masonry
- C1600/C1600M Specification for Rapid Hardening Hydraulic Cement
- E72 Test Methods of Conducting Strength Tests of Panels for Building Construction
- E96/E96M Test Methods for Water Vapor Transmission of Materials
- E119 Test Methods for Fire Tests of Building Construction and Materials
- E447 Test Method for Compressive Strength of Laboratory Constructed Masonry Prisms (Withdrawn 1997)³
- E514/E514M Test Method for Water Penetration and Leakage Through Masonry
- E518/E518M Test Methods for Flexural Bond Strength of Masonry
- E519/E519M Test Method for Diagonal Tension (Shear) in Masonry Assemblages

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology C1180 and Terminology C1232.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *surface bonding mortar, n*—a product containing hydraulic cement, glass fiber reinforcement with or without inorganic fillers, or organic modifiers in a prepackaged form requiring only the addition of water prior to application.

4. Materials and Manufacture

4.1 The materials used as ingredients in packaged, dry, combined materials for surface bonding mortar shall conform to the following requirements:

4.1.1 *Hydraulic Cements*—Hydraulic cements used shall conform to the following ASTM specifications:

4.1.1.1 *Portland Cement*—Type I, IA, II, IIA, III, or IIIA of Specification C150/C150M.

4.1.1.2 *Blended Hydraulic Cements*—Type IS, ISA, IP, or IPA of Specification C595/C595M.

4.1.1.3 *Hydraulic Cement*—Type GU, HE, MS, or MH of Specification C1157/C1157M.

4.1.1.4 *Masonry Cement*—Specification C91/C91M.

4.1.1.5 *Rapid Hardening Hydraulic Cement*, Type GRH, MRH, VRH, or URH of Specification C1600/C1600M.

4.1.2 *Hydrated Lime*—Type S or SA of Specification C207.

4.1.3 *Pozzolan*—Class N, F, or C of Specification C618.

4.1.4 *Aggregates*—Aggregates shall conform to Specification C144 with the exception of grading. The maximum allowable particle size shall not exceed one third of the

recommended application thickness of the surface bonding mortar with uniform distribution of particle size.

4.1.4.1 All aggregates shall be dried, without decomposition, to a moisture content of less than 0.1 weight %, computed on material dried substantially to constant weight at 221 to 230°F (105 to 110°C).

4.1.5 *Glass Fibers*—Glass fibers shall be chopped strands of a minimum ½-in. (13-mm) length to provide significant reinforcement in a cementitious matrix.

4.1.5.1 Glass fibers for use in surface bonding mortar, that will be subjected to wetting, humid atmosphere, or contact with moist ground have the potential to react with the available alkalies present in the portland-cement matrix, causing strength reduction of the surface bonding mortar.

4.1.5.2 The producer shall show evidence satisfactory to the purchaser that glass composition, cement matrix, or both, have been designed to reduce significantly or eliminate this unfavorable reaction.

4.1.6 *Additives*—Additives may be added as part of the packaged, dry, combined materials for purposes such as plasticity, air entrainment, water repellency, set acceleration, chemical bonding, and coloring. See Specifications C260/C260M and C494/C494M.

4.1.6.1 Admixtures or mortar colors shall not be added to the surface bonding mortars at the time of mixing unless provided for in the contract specifications, and, after the materials are so added, the surface bonding mortars shall conform to the physical requirements prescribed in Table 1.

4.1.6.2 *Antifreeze Compounds*—No antifreeze liquid, salts, or other substances shall be used in surface bonding mortar to lower the freezing point.

NOTE 1—Calcium chloride, when provided for in the contract specifications, and expressly recommended by the manufacturer, may be used as an accelerator in amounts not exceeding ½ % by weight of the total bag weight.

5. Proportioning

5.1 The proportions of materials such as hydraulic cements, aggregate, and glass fibers shall be such that the requirements

TABLE 1 Physical Requirements

Flexural Strength^A (average of three prisms)

The flexural strength of prisms of surface bonding mortar prepared and tested in accordance with this specification shall be equal to or higher than the values specified for the ages indicated as follows:

	psi	(MPa)
1 day	450	3.1
7 days	700	4.8
28 days	800	5.5

Compressive Strength (average of prisms broken in flexure)

The compressive strength of modified cubes of surface bonding mortar prepared and tested in accordance with this specification shall be equal to or higher than the values specified for the ages indicated as follows:

	psi	(MPa)
1 day	1600	11
28 days	3500	24.1

Time of setting, Vicat needle, initial set, minimum, min	45
final set, max, h	8
Water retention flow after suction, min, % of original flow, min	75

³ The last approved version of this historical standard is referenced on www.astm.org.