



Designation: D2996 – 23

Standard Specification for Filament-Wound “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe¹

This standard is issued under the fixed designation D2996; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers machine-made reinforced thermosetting resin pressure pipe (RTRP) manufactured by the filament winding process up to 60 in. nominal size. Included are a classification system and requirements for materials, mechanical properties, dimensions, performance, methods of test, and marking.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are provided for information purposes only.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—The term “fiberglass pipe” as described in Section 3 of this specification applies to both reinforced thermosetting resin pipe (RTRP) and reinforced polymer mortar pipe (RPMP). This specification covers only reinforced thermosetting resin pipe (RTRP).

NOTE 2—There is no known ISO equivalent to this standard.

NOTE 3—This specification is applicable to RTRP where the ratio of outside diameter to wall thickness is 10:1 or more.

NOTE 4—For the purposes of this standard, polymer does not include natural polymers.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.23 on Reinforced Thermosetting Resin Piping Systems and Chemical Equipment.

Current edition approved Oct. 1, 2023. Published October 2023. Originally approved in 1971. Last previous edition approved in 2017 as D2996 – 17. DOI: 10.1520/D2996-23.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics
- D883 Terminology Relating to Plastics
- D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure
- D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D2105 Test Method for Longitudinal Tensile Properties of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Tube
- D2143 Test Method for Cyclic Pressure Strength of Reinforced, Thermosetting Plastic Pipe
- D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading
- D2992 Practice for Obtaining Hydrostatic or Pressure Design Basis for “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Fittings
- D3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings
- F412 Terminology Relating to Plastic Piping Systems

3. Terminology

3.1 Definitions:

3.1.1 *General*—Definitions are in accordance with Terminologies D883 and F412 and abbreviations are in accordance with Terminology D1600, unless otherwise indicated. The abbreviation for reinforced thermosetting resin pipe is RTRP.

3.2 Definitions of Terms Specific to This Standard:

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

3.2.1 *coating*—a resin layer, with or without filler or reinforcement, or both, applied to the exterior surface of the pipe structural wall.

3.2.2 *fiberglass pipe*—a tubular product containing glass-fiber reinforcements embedded in or surrounded by cured thermosetting resin; the composite structure may contain aggregate, granular or platelet fillers, thixotropic agents, pigments, or dyes; thermoplastic or thermosetting liners or coatings may be included.

3.2.3 *filament winding*—a process used to manufacture tubular goods by winding continuous fibrous glass strand roving, or roving tape, saturated with liquid resin or preimpregnated with partially cured resin (subsequent heating may be required to polymerize the resin system) onto the outside of a mandrel in a predetermined pattern under controlled tension; the inside diameter (ID) of the pipe is fixed by the mandrel outside diameter and the outside diameter (OD) of the pipe is determined by the amount of material that is wound on the mandrel.

3.2.4 *liner*—the inner portion of the wall at least 0.005 in. (0.13 mm) in thickness, as determined in 8.3.2, which does not contribute to the strength in the determination of the hydrostatic design basis.

3.2.5 *reinforced polymer mortar pipe (RPMP)*—a fiberglass pipe with aggregate.

3.2.6 *reinforced thermosetting resin pipe (RTRP)*—a fiberglass pipe without aggregate.

3.2.7 *reinforced wall thickness*—the total wall thickness minus the liner or exterior coating thickness, or both.

4. Classification

4.1 *General*—Pipe meeting this specification is classified by type, grade, class, and hydrostatic design basis and by a secondary cell classification system that defines the basic mechanical properties of the pipe. These types, grades, classes, hydrostatic design basis categories, and cell classification designations are as follows:

4.1.1 *Types*:—Type 1

Filament wound.

4.1.2 *Grades*:—Grade 1

Glass fiber reinforced epoxy resin pipe.

Grade 2—Glass fiber reinforced polyester resin pipe.

Grade 7—Glass fiber reinforced furan resin pipe.

TABLE 1 Hydrostatic Design Basis Categories

Cyclic Test Method		Static Test Method	
Designation	Hoop Stress, psi (MPa)	Designation	Hoop Stress, psi (MPa)
A	2 500 (17.2)	Q	5 000 (34.5)
B	3 150 (21.7)	R	6 300 (43.4)
C	4 000 (27.6)	S	8 000 (55.2)
D	5 000 (34.5)	T	10 000 (68.9)
E	6 300 (43.4)	U	12 500 (86.2)
F	8 000 (55.2)	W	16 000 (110)
G	10 000 (68.9)	X	20 000 (138)
H	12 500 (86.2)	Y	25 000 (172)
		Z	31 500 (217)

4.1.3 *Classes*:—Class A

No liner.

Class B—Polyester resin liner (nonreinforced).

Class C—Epoxy resin liner (nonreinforced).

Class E—Polyester resin liner (reinforced).

Class F—Epoxy resin liner (reinforced).

Class H—Thermoplastic resin liner (specify).

Class I—Furan resin liner (reinforced).

4.1.4 *Hydrostatic Design Basis*—Two methods of classifying the hydrostatic design basis of the pipe are provided. Pipe meeting this specification shall be classified using either the cyclic test method or the static test method, or both, and the designations as shown in Table 1. Appendix X1 explains how these design basis categories are to be used.

4.1.4.1 For pipe subjected to axial or end loads, the effect of these loads shall be represented in the HDB testing. In the designation code, the numeral 1 shall immediately follow the HDB letter class if free-end type closures were used and the numeral 2 shall immediately follow the HDB letter class if restrained-end type closures were used to establish the HDB.

4.1.5 *Mechanical Properties*—Table 2 presents a cell classification system for identifying the mechanical properties of pipe covered by this specification.

NOTE 5—For the purposes of this classification, polyester resins shall include vinylester resins, but the purchaser should consult with the manufacturer to determine which resin is applicable for the specific conditions in which the pipe will be used.

NOTE 6—All possible combinations covered by the above classification system may not be commercially available.

TABLE 2 Physical Property Requirements

Designation Order Number	Mechanical Property	Cell Limits						
		0	1	2	3	4	5	6
1	Short-term rupture strength hoop tensile stress, min, psi (MPa)	...	10 000 (68.9)	30 000 (207)	40 000 (276)	50 000 (345)	60 000 (414)	70 000 (483)
2	Longitudinal tensile strength min, psi (MPa)	...	8000 (55.2)	15 000 (103)	25 000 (172)	35 000 (241)	45 000 (310)	55 000 (379)
3	Longitudinal tensile modulus, min, psi $\times 10^6$ (MPa)	...	1 (6900)	2 (13 000)	3 (20 700)	4 (27 600)	5 (34 500)	6 (41 400)
4	Pipe stiffness at 5 % deflection, min, psi (kPa)	...	5 (34)	9 (62)	18 (124)	36 (248)	72 (496)	144 (993)