



Designation: D3276 – 21

Standard Guide for Painting Inspectors (Metal Substrates)¹

This standard is issued under the fixed designation D3276; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide is intended as an information aid to painting inspectors in carrying out their task efficiently. It includes the key elements of surface preparation, coatings application, and final approval for both field and shop work. The items should be selected that are pertinent to the specification of a particular job.

NOTE 1—For additional helpful information, refer to the following documents:

*Manual of Coating Work for Light-Water Nuclear Power Plant Primary Containment and Other Safety-Related Facilities*²

*New Concepts for Coating Protection of Steel Structures*³

D16 Terminology for Paint, Related Coatings, Materials, and Applications⁴

D4538 Terminology Relating to Protective Coatings and Lining Work for Power Generation Facilities⁴

Steel Structures Painting Manual Vol 1 Good Painting Practice⁵

Steel Structures Painting Manual Vol 2 Systems and Specifications⁵

Manufacturers Specifications and Instructions (made available to the inspector for reference to special requirements for proper application)

Safety Data Sheets (needed to ensure that personnel take necessary precautions in handling hazardous materials). Available from Materials manufacturer.

1.2 Certain industries or owners may require certified inspection personnel. See Guide **D4537** for establishing procedures to certify inspectors for coatings work in nuclear facilities.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

¹ This guide is under the jurisdiction of ASTM Committee **D01** on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee **D01.46** on Industrial Protective Coatings.

Current edition approved Nov. 1, 2021. Published December 2021. Originally approved in 1973. Last previous edition approved in 2015 as D3276 – 15^{ε1}. DOI: 10.1520/D3276-21.

² ASTM, 1979.

³ ASTM STP 841, ASTM, 1984.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁵ Available from Association for Materials Protection and Performance (AMPP), 15835 Park Ten Place, Houston, TX 77084, <https://www.ampp.org>.

1.4 This guide is arranged in the following order:

	Section
Referenced Documents	2
ASTM Standards	2.1
OSHA Standards	2.2
Steel Structures Painting Council Publications	2.3
International Standards Organization (ISO)	2.4
ASTM Adjuncts	2.6
Significance and Use	3
Preparation for Inspection	4
Surface Preparation Methods and Requirements	5
Surface Preparation	5.1
Pictorial Standard D2200	5.1.1
Factors Affecting Coating Performance	5.2
Cleanliness	5.2.1
Mill Scale	5.2.2
Surface Profile	5.2.3
Sharp Edges	5.2.4
Cleaning Procedures	5.3
Chemical Cleaning	5.3.1
Solvent Vapor Cleaning	5.3.1.1
Hand Tool Cleaning	5.3.2
Power Tool Cleaning	5.3.3
Power Tool Cleaning to Bare Metal	5.3.4
Commercial Grade Power Tool Cleaning	5.3.4.4
Blast Cleaning	5.3.5
Pressurized Water Cleaning	5.3.6
Cleaning and Preparation of Various Surfaces	5.4
Steel Surfaces	5.4.1
Galvanized Surfaces	5.4.2
Aluminum Surfaces	5.4.3
Precautions in Preparing Unpainted and Previously Painted Surfaces	5.4.4
Inspection of Surfaces Prior to Field Painting	5.5
New Construction	5.5.1
Maintenance Repainting	5.5.2
Coating Storage and Handling	6
Storage of Coating and Thinner	6.1
Mixing of Coatings	6.2
Thinning	6.3
Initial Samples	6.3.1
Thinning of Coating	6.3.2
Sampling of Thinned Coating	6.3.3
Heating of Coating	6.4
Weather Considerations	7
Drying	7.1
Low Temperature	7.2
High Temperature	7.3
Moisture	7.4
Wind	7.5
Coating Application	8
Residual Contaminants	8.1
Quality Assurance	8.2
Film Defects	8.2.1
Brush Application	8.3
Spray Application	8.4

Roller Application	8.5
Miscellaneous Methods	8.6
Rate of Application	8.7
Additional Considerations	9
Ventilation	9.1
Shopcoat Repair	9.2
Painting Schedule	9.3
Film Integrity	9.4
Recoat Time	9.5
Coating System Failure	9.6
Inspection Equipment	10
General	10.1
Surface Profile Gages	10.1.1
Adhesion of Existing Coating	10.1.2
Portable Pull-Off Adhesion Testers	10.1.3
Field Inspection Equipment	10.2
Drying and Curing Times	10.2.1
Thermometers	10.2.1.1
Relative Humidity and Dew Point	10.2.1.2
Wet-Film Thickness Gages	10.2.2
Interchemical Gage	10.2.2.1
Notched Gage	10.2.2.2
Dry-Film Thickness Gages	10.2.3
Nondestructive Film Thickness Gages	10.2.3.1
Magnetic-Type Gages	10.2.3.2
Current-Type Gages	10.2.3.3
Destructive Thickness Gage	10.2.3.4
Holiday Detectors	10.2.4
Comparison of Surface Preparation	
Specifications	Table 1
Comparison of Water Jetting Standards	Table 2
Inspection Checklist	Appendix X1

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:⁴

- D16** Terminology for Paint, Related Coatings, Materials, and Applications
- D1212** Test Methods for Measurement of Wet Film Thickness of Organic Coatings
- D1730** Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting
- D2200** Practice for Use of Pictorial Surface Preparation Standards and Guides for Painting Steel Surfaces
- D3359** Test Methods for Rating Adhesion by Tape Test
- D3363** Test Method for Film Hardness by Pencil Test
- D4138** Practices for Measurement of Dry Film Thickness of Protective Coating Systems by Destructive, Cross-Sectioning Means
- D4212** Test Method for Viscosity by Dip-Type Viscosity Cups
- D4285** Test Method for Indicating Oil or Water in Compressed Air
- D4414** Practice for Measurement of Wet Film Thickness by Notch Gages
- D4417** Test Methods for Field Measurement of Surface

Profile of Blast Cleaned Steel

- D4537** Guide for Establishing Procedures to Qualify and Certify Personnel Performing Coating and Lining Work Inspection in Nuclear Facilities
 - D4538** Terminology Relating to Protective Coating and Lining Work for Power Generation Facilities
 - D4541** Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers
 - D4752** Practice for Measuring MEK Resistance of Ethyl Silicate (Inorganic) Zinc-Rich Primers by Solvent Rub
 - D4940** Test Method for Conductometric Analysis of Water Soluble Ionic Contamination of Blast Cleaning Abrasives
 - D5064** Practice for Conducting a Patch Test to Assess Coating Compatibility
 - D5162** Practice for Discontinuity (Holiday) Testing of Nonconductive Protective Coating on Metallic Substrates
 - D5402** Practice for Assessing the Solvent Resistance of Organic Coatings Using Solvent Rubs
 - D6386** Practice for Preparation of Zinc (Hot-Dip Galvanized) Coated Iron and Steel Product and Hardware Surfaces for Painting
 - D6677** Test Method for Evaluating Adhesion by Knife
 - D6913** Test Methods for Particle-Size Distribution (Gradation) of Soils Using Sieve Analysis
 - D7091** Practice for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to Ferrous Metals and Nonmagnetic, Nonconductive Coatings Applied to Non-Ferrous Metals
 - D7127** Test Method for Measurement of Surface Roughness of Abrasive Blast Cleaned Metal Surfaces Using a Portable Stylus Instrument (Withdrawn 2021)⁶
 - D7393** Practice for Indicating Oil in Abrasives
 - E337** Test Method for Measuring Humidity with a Psychrometer (the Measurement of Wet- and Dry-Bulb Temperatures)
- 2.2 *OSHA Standard:*⁵
- 29 CFR 1926.59** Hazard Communication
- 2.3 *SSPC Standards:*⁵
- SSPC-AB 1** Mineral and Slag Abrasives
 - SSPC-AB 2** Cleanliness of Recycled Ferrous Metallic Abrasives
 - SSPC-AB 3** Newly Manufactured or Re-Manufactured Steel Abrasives
 - SSPC-AB 4** Recyclable Encapsulated Abrasive Media
 - SSPC-SP 1** Solvent Cleaning
 - SSPC-SP 2** Hand Tool Cleaning
 - SSPC-SP 3** Power Tool Cleaning
 - SSPC-SP 5/NACE No. 1** White Metal Blast Cleaning
 - SSPC-SP 6/NACE No. 3** Commercial Blast Cleaning
 - SSPC-SP 7/NACE No. 4** Brush-off Blast Cleaning
 - SSPC-SP 8** Pickling
 - SSPC-SP 10/NACE No. 2** Near-White Blast Cleaning
 - SSPC-SP 11** Power Tool Cleaning to Bare Metal
 - SSPC-SP 14/NACE No. 8** Industrial Blast Cleaning
 - SSPC-SP 15** Commercial Grade Power Tool Cleaning

⁶ The last approved version of this historical standard is referenced on www.astm.org.