



Designation: D3564 – 22

Standard Practice for Application of Floor Polishes to Maintain Vinyl Composition Tile or Flooring¹

This standard is issued under the fixed designation D3564; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the application of floor polishes to maintain vinyl composition tile or flooring. Floor polishes are applied to vinyl composition tile floors for protection and beautification of the floor surface. Cleaning, polish application, removal, and maintenance procedures are important functions in this process.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Significance and Use

2.1 Vinyl composition tile or flooring consists of vinyl resins (suitably plasticized and stabilized) fortified with composition fibers, mineral fillers, and prime pigments. In some cases, all or part of the wearing surfaces may consist of unfilled vinyl resin that is clear or translucent. Metallic accents (chips, pigment, etc.) are frequently used to form the overall design. In general, the overall binder content is lower than that of homogeneous vinyl tile. For the purpose of this practice, vinyl composition also includes vinyl asbestos tile.

3. Initial Treatment, New Floors

3.1 Do not scrub vinyl composition tile floors for about 4 to 5 days after the floor has been installed. This waiting period

¹ This practice is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.05 on Specifications.

Current edition approved Jan. 1, 2022. Published February 2022. Originally approved in 1977. Last previous edition approved in 2015 as D3564 – 95(2015). DOI: 10.1520/D3564-22.

allows sufficient time for the adhesive to set properly. However, it is good practice to clean the floor lightly and apply a polish as soon as it has been installed. Lightly mop with a dilute floor cleaner solution (following the manufacturer's dilution recommendations for damp mopping) to remove surface soil, and then apply one or two coats of a floor polish. Care should be taken during these operations not to flood the floor resulting in excess polish being "worked into" the seams or joints in the flooring.

3.2 Sweep the floor frequently to keep it free of foreign matter, dust, and dirt.

3.2.1 For this purpose, treated mops or dust cloths may be used provided they are treated in such a manner that no deposits of treatment compound are left on the floor.

4. Thorough Cleaning

4.1 After the 4 to 5 day waiting period on new floors or as needed on previously installed floors, scrub thoroughly to remove all dirt, surface soil, temporary floor polish coats, etc.

4.2 Use a suitable floor cleaner solution in accordance with the manufacturer's instructions.

4.2.1 Do not use cleaner solutions containing abrasives or aromatic or aliphatic petroleum distillates. Alkaline cleaner solutions with a pH higher than eleven at the use concentrations are not recommended.

4.3 Apply the cleaner solution without flooding the floor.

4.4 Allow the cleaner solution to remain on the floor undisturbed for a few minutes but not long enough for it to dry.

4.5 Scrub until all dirt and soil is loosened from the floor. Power machines fitted with a scrub brush or a very mild scrubbing type of synthetic pad may be used to hasten the cleaning action. Avoid coarse grades of synthetic pads or steel wool to prevent tile damage.

4.6 After scrubbing, take up the cleaner solution using a mop or wet vacuum.

4.7 Rinse the floor thoroughly with clean, cool water but do not flood the floor during this operation. The purpose is to remove all traces of the cleaner solution and soil so that the performance of any subsequent coating is not adversely affected. Take up the rinse water.