



Designation: D4699 – 23

Standard Test Method for Vibratory Packing Density of Large Formed Catalyst and Catalyst Carrier Particles¹

This standard is issued under the fixed designation D4699; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the vibratory packing density of formed catalyst and catalyst carrier particles that will not break up significantly under test conditions. For the purpose of this test, catalyst particles are defined as extrudates, spheres or formed pellets greater than 4.8 mm.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[B215 Practices for Sampling Metal Powders](#)

[D3766 Terminology Relating to Catalysts and Catalysis](#)

[E105 Guide for Probability Sampling of Materials](#)

[E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E456 Terminology Relating to Quality and Statistics](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

[E1272 Specification for Laboratory Glass Graduated Cylinders](#)

3. Terminology

3.1 *Definitions*—See Terminology [D3766](#).

4. Summary of Test Method

4.1 A known sample of environmentally equilibrated formed catalyst or catalyst carrier particles is vibrated in a graduated cylinder. The vibratory packing density is determined for a specified drying condition.

5. Significance and Use

5.1 This test method is used for measuring the vibratory packing density of formed particles used in fixed bed reactors, driers, and so forth.

6. Apparatus

6.1 *Graduated Cylinder*, capacity 2000-mL.

6.2 *Vibratory Plate*.³

6.3 *Desiccator*, with a desiccant grade molecular sieve such as 4A.

6.4 *Balance*, having a sensitivity of 1.0 g.

6.5 *Balance*, having a sensitivity of 0.1 g.

6.6 *Drying Oven*.

7. Sampling

7.1 Test sample(s) shall be obtained from larger composites by riffing or splitting in accordance with subsection 5.12 of STP 447A⁴ with the aim of obtaining a representative sample that mirrors the shape and size distribution of the larger

¹ This test method is under the jurisdiction of ASTM Committee [D32](#) on Catalysts and is the direct responsibility of Subcommittee [D32.02](#) on Physical-Mechanical Properties.

Current edition approved Oct. 1, 2023. Published October 2023. Originally approved in 1987. Last previous edition approved in 2018 as D4699 – 03 (2018) ^{ϵ 1}. DOI: 10.1520/D4699-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The sole source of supply of the Syntron Vibrating Machine, Model V-2-B with Power Pulse Controller, known to the committee at this time is FMC Technologies, 57 Cooper Ave., Homer City, PA 15748–9234. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee¹, which you may attend.

⁴ Manual on Test Sieving Methods, ASTM STP 447A, ASTM International, 2005.