



# Standard Test Methods for Polyurethane Raw Materials: Determination of Viscosity of Crude or Modified Isocyanates<sup>1</sup>

This standard is issued under the fixed designation D4889; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 These test methods (A and B) determine the viscosity of crude or modified *isocyanates*. They are applicable to products derived from toluene diisocyanate, methylene di(phenylisocyanate), and polymeric (methylene phenylisocyanate) (see **Note 1**).

**NOTE 1**—Test method A includes a procedure for measuring dynamic viscosity using a rotational instrument. Test method B is simply a reference to a general procedure for measuring kinematic viscosity, **D445**.

1.2 The values stated in SI units are to be regarded as standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazards statement, see **Warning** at the end of **5.1**.

**NOTE 2**—This standard is equivalent to ISO 3219 and ISO 3104.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**D445** Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)

**D883** Terminology Relating to Plastics

**E2251** Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids

2.2 *ISO Standards*:<sup>3</sup>

**ISO 3104** Petroleum Products—Transparent and Opaque Liquids—Determination of Kinematic Viscosity and Cal-

ulation of Dynamic Viscosity

**ISO 3219** Plastics—Polymers/Resins in the Liquid State or as Emulsions or Dispersions—Determination of Viscosity Using a Rotational Viscometer with Defined Shear Rate

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in these test methods see Terminology **D883**.

## 4. Significance and Use

4.1 These test methods can be used for research, quality control, or specification tests to characterize *isocyanates* used in polyurethane products.

4.2 Viscosity measures the resistance of a fluid to uniform continuous flow without turbulence or other forces.

4.3 Some isocyanates exhibit non-Newtonian behavior under certain conditions. Whenever possible, generate results for comparison under the same conditions, that is, the same spindle/speed combination for rotational viscosity and the same tube size for kinematic viscosity.

## 5. Sampling

5.1 Since organic *isocyanates* react with atmospheric moisture, take special precautions in sampling. Usual sampling methods, even when conducted rapidly, can cause contamination of the sample with insoluble urea. Therefore, blanket the sample with dry air or nitrogen at all times. (**Warning**—*Diisocyanates* are eye, skin and respiratory irritants at concentrations above the occupational exposure limit (TLV or PEL). *Diisocyanates* can cause skin and respiratory sensitization (asthma) in some people. Once sensitized, it is essential to limit further exposure to diisocyanates. Use a combination of engineering controls and personal protective equipment, including respiratory, skin and eye protection, to prevent over-exposure to diisocyanates. Consult the product suppliers' Safety Data Sheet (SDS) for more detailed information about potential health effects and other specific safety and handling instructions for the product.)

## 6. Test Conditions

6.1 Since isocyanates react with moisture, keep laboratory humidity low, preferably about 50 % relative humidity. See **Warning** in **5.1**.

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee **D20** on Plastics and are the direct responsibility of Subcommittee **D20.22** on Cellular Materials - Plastics and Elastomers.

Current edition approved May 1, 2015. Published March 2011. Originally approved in 1988. Last previous edition approved in 2011 as D4889 - 04(2011). DOI: 10.1520/D4889-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.