



Designation: D5155 – 19

Standard Test Methods for Polyurethane Raw Materials: Determination of the Isocyanate Content of Aromatic Isocyanates¹

This standard is issued under the fixed designation D5155; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 These test methods are used to measure the isocyanate content of aromatic isocyanates used as polyurethane raw materials.

1.1.1 *Test Method A*—Unheated toluene-dibutylamine determines the toluene diisocyanate content, the amine equivalent and the isocyanate content of refined toluene-2,4-diisocyanate and toluene-2,6-diisocyanate, or mixtures of the two. Other isomers, if present, will be included in the determination. This test method is also applicable to other isocyanates of suitable reactivity and solubility.

1.1.2 *Test Method B*—Heated toluene-dibutylamine determines the amine equivalent and the isocyanate content of crude or modified isocyanates derived from toluene diisocyanate, methylene di-(4-phenylisocyanate) and polymeric (methylene phenylisocyanate).

1.1.3 *Test Method C*—Unheated trichlorobenzene-toluene-dibutylamine determines the amine equivalent and the isocyanate content of crude or modified isocyanates derived from toluene diisocyanate, methylene-di-(4-phenylisocyanate) and polymeric (methylene phenylisocyanate).

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—Method C of this test method is equivalent to Method B of ISO 14896.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recom-*

mendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards*:²

D883 Terminology Relating to Plastics

D1193 Specification for Reagent Water

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³

E456 Terminology Relating to Quality and Statistics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E2935 Practice for Conducting Equivalence Testing in Laboratory Applications

2.2 *ISO Standard*:

ISO 14896 Polyurethane Raw Materials-Determination of Isocyanate Content

3. Terminology

3.1 *Definitions*—Terms used in this standard are defined in accordance with Terminology D883, unless otherwise specified. For terms relating to precision and bias and associated issues, the terms used in this standard are defined in accordance with Terminology E456.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *amine equivalent*—the weight of sample that will combine with 1.0-g equivalent weight of dibutylamine.

3.2.2 *assay*—the percent by weight of toluene diisocyanate present in the sample.

3.2.3 *isocyanate (NCO) content*—the percent by weight of NCO groups present in the sample.

4. Summary of Test Methods

4.1 In all three test methods, the isocyanate sample is reacted with an excess amount of dibutylamine to form the

¹ These test methods are under the jurisdiction of ASTM Committee D20 on Plastics and are the direct responsibility of Subcommittee D20.22 on Cellular Materials - Plastics and Elastomers.

Current edition approved Aug. 1, 2019. Published August 2019. Originally approved in 1991. Last previous edition approved in 2014 as D5155 - 14^{e1}. DOI: 10.1520/D5155-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

corresponding urea. The NCO content is determined from the amount of dibutylamine consumed in the reaction. The test methods differ in the reaction conditions, or solvents used, or both.

4.1.1 Test Method A—The sample is added to an excess amount of dibutylamine in toluene and allowed to stand at room temperature for 15 min. The reaction mixture is diluted with isopropyl alcohol, and the excess dibutylamine is back-titrated with hydrochloric acid.

4.1.2 Test Method B—The sample is added to an excess amount of dibutylamine in toluene and stirred for 20 min. The resulting solution is then heated rapidly to 100°C, removed from the heat, and allowed to stand for 30 min. The reaction mixture is diluted with isopropyl alcohol, and the excess dibutylamine is back-titrated with hydrochloric acid.

4.1.3 Test Method C—The sample is added to an excess amount of dibutylamine in toluene and trichlorobenzene. The resulting solution is allowed to stand until it has cooled to room temperature. The reaction mixture is diluted with methanol and back-titrated with hydrochloric acid.

5. Significance and Use

5.1 These test methods are to be used for research or for quality control to characterize isocyanates used in polyurethane products.

6. Interferences

6.1 Phosgene, the carbamyl chloride of the isocyanate, hydrogen chloride, and any other acidic or basic compounds will interfere. In refined isocyanates, these impurities are usually present in such low amounts that they do not affect the determination. While some crude or modified isocyanates contain acidities of up to approximately 0.05 %, the NCO content is not normally corrected.

7. Reagents and Materials

7.1 Purity of Reagents—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades are allowed, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 Purity of Water—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Types I through IV of Specification D1193.

8. Sampling

8.1 Since organic isocyanates react with atmospheric moisture, take special precautions in sampling. Usual sampling methods, even when conducted rapidly, can cause contamination

of the sample with insoluble urea. Therefore, blanket the sample with dry air or nitrogen at all times. (**Warning**—Diisocyanates are eye, skin and respiratory irritants at concentrations above the occupational exposure limit (TLV or PEL). Diisocyanates can cause skin and respiratory sensitization (asthma) in some people. Once sensitized, further exposure to diisocyanates should be eliminated. A combination of engineering controls and personal protective equipment, including respiratory, skin and eye protection, may be used to prevent over-exposure to diisocyanates. Consult the product suppliers' Safety Data Sheet (SDS) for more detailed information about potential health effects and other specific safety and handling instructions for the product.)

9. Test Conditions

9.1 Since isocyanates react with moisture, keep the laboratory humidity low, preferably below 50 % relative humidity.

TEST METHOD A—UNHEATED TOLUENE-DIBUTYLAMINE

10. Apparatus

10.1 Any weighing device that weighs a liquid by difference to the nearest 0.001 g.

10.2 *Cooling Bath*—Any container approximately 50 mm deep filled with ice and water.

10.3 Pipet capable of reproducibly delivering $50 \pm .05$ mL.

10.4 Buret capable of dispensing 0.05 mL at a time.

11. Reagents

11.1 Bromocresol Green Indicator Solution—Using 1.5 mL of 0.1 N sodium hydroxide, extract the bromocresol green from 0.100 g of bromocresol green indicator-grade powder, stirring vigorously until the amount of insoluble residue remains constant. Decant the aqueous portion into a 100-mL volumetric flask and dilute to the mark with water.

11.2 Dibutylamine Solution (260 g/L)—Dilute 260 g of dry dibutylamine to 1 L with dry toluene. Dry the solution with a drying agent.⁵

11.3 Hydrochloric Acid (1 N)—Prepare 1 N HCl (hydrochloric acid) and standardize frequently enough to detect changes of 0.001 N.

11.4 Isopropyl Alcohol.

11.5 Toluene, dry with a drying agent.⁵

12. Procedure

12.1 Run sample and blank determinations side by side. Run the blank determination exactly as described in 12.2 – 12.4, but without adding the sample.

12.2 Add a magnetic stirring bar and 40 mL of dry toluene to a 500-mL Erlenmeyer flask that has been rinsed successively with water, alcohol, and high-purity acetone, dried at 100°C,

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

⁵ The 4A Molecular Sieve, or its equivalent, has been found suitable. The 4A Molecular Sieve is available from VWR International, Inc., 1310 Goshen Parkway, West Chester, PA 19380.