



Designation: D6925 – 23

Standard Test Method for Preparation and Determination of the Relative Density of Asphalt Mix Specimens by Means of the Superpave Gyratory Compactor¹

This standard is issued under the fixed designation D6925; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the compaction of an asphalt mix into cylindrical specimens using the Superpave Gyratory Compactor (SGC). This standard also refers to the determination of the relative density of the compacted specimens at any point in the compaction process. Compacted specimens are suitable for volumetric, physical property, and mechanical testing. Smaller specimens may be cut from the compacted cylindrical specimen for specific test specimen geometry requirements. The compaction procedures apply to Laboratory Mixed Laboratory Compacted (LMLC) and Plant Mixed Laboratory Compacted (PMLC) asphalt mix.

1.2 The values stated in SI units are to be regarded as standard. The values given in degrees for the angle of gyration, gyrations per minute, and hardness are mathematical conversions from the SI units and are provided for information regarding the commonly used units of degree, rotations per minute, and Rockwell hardness, respectfully.

1.3 The text of this test method references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D8 Terminology Relating to Materials for Roads and Pavements
- D979/D979M Practice for Sampling Asphalt Mixtures
- D1188/D1188M Test Method for Bulk Specific Gravity and Density of Compacted Asphalt Mixtures Using Coated Samples
- D2041/D2041M Test Method for Theoretical Maximum Specific Gravity and Density of Asphalt Mixtures
- D2726/D2726M Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Asphalt Mixtures
- D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials
- D4402/D4402M Test Method for Viscosity Determination of Asphalt at Elevated Temperatures Using a Rotational Viscometer
- D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing
- D6752/D6752M Test Method for Bulk Specific Gravity and Density of Compacted Asphalt Mixtures Using Automatic Vacuum Sealing Method
- D6857/D6857M Test Method for Maximum Specific Gravity and Density of Asphalt Mixtures Using Automatic Vacuum Sealing Method
- D7115 Test Method for Measurement of Superpave Gyratory Compactor (SGC) Internal Angle of Gyration Using Simulated Loading
- E10 Test Method for Brinell Hardness of Metallic Materials
- E18 Test Methods for Rockwell Hardness of Metallic Materials
- E2251 Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids

¹ This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.20 on Mechanical Tests of Asphalt Mixtures.

Current edition approved Dec. 1, 2023. Published January 2024. Originally approved in 2003. Last previous edition approved in 2015 as D6925 – 15. DOI: 10.1520/D6925-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 AASHTO Standards:³

- R 18** Standard Practice for Establishing and Implementing a Quality Management System for Construction Materials Testing Laboratories
- R 99** Standard Practice for Troubleshooting Asphalt Specimen Volumetric Differences between Superpave Gyratory Compactors (SGCs) Used in the Design and the Field Management of Superpave Mixtures
- R 30** Standard Practice for Mixture Conditioning of Hot Mix Asphalt (HMA)
- R 35** Standard Practice for Superpave Volumetric Design for Hot Mix Asphalt (HMA)
- R 47** Standard Practice for Reducing Samples of Hot Mix Asphalt (HMA) to Testing Size
- T 312** Standard Method of Test for Preparing and Determining the Density of Hot-Mix Asphalt (HMA) Specimens by Means of the Superpave Gyratory Compactor
- T 344** Standard Method of Test for Evaluation of Superpave Gyratory Compactor (SGC) Internal Angle of Gyration Using Simulated Loading

2.3 Other References:

- ASME B46.1** Surface Texture (Surface Roughness, Waviness, and Lay)⁴
- Asphalt Institute MS-2** Mix Design Methods for Asphalt Concrete⁵

3. Terminology

3.1 This test method uses terms as defined by Terminology **D8**.

4. Significance and Use

4.1 This test method is used to prepare specimens for determining the volumetric and physical properties of compacted asphalt mix.

4.2 This test method is useful for monitoring the density of test specimens during the compaction process. This test method is suited for the laboratory design, field control of asphalt mix, forensics, imaging, and visualization of compacted asphalt mix.

NOTE 1—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Specification **D3666** are generally considered capable of competent and objective testing, sampling, inspection, etc. Users of this standard are cautioned that compliance with Specification **D3666** alone does not completely ensure reliable results. Reliable results depend on many factors; following the suggestions of Specification **D3666** or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

³ Available from American Association of State Highway and Transportation Officials (AASHTO), 444 N. Capitol St., NW, Suite 249, Washington, DC 20001, <http://www.transportation.org>.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁵ Available from Asphalt Institute, 2696 Research Park Dr., Lexington, KY 40511, <http://www.asphaltinstitute.org>.

5. Apparatus

5.1 *Superpave Gyratory Compactor*—A compactor comprised of the following system components: (1) reaction frame and drive system, (2) loading system, loading ram, and pressure indicator, and (3) recording system for height measurement and number of gyrations.

5.1.1 The reaction frame shall provide a structure against which the compaction pressure can be applied when compacting specimens.

5.1.2 The compactor shall be designed to gyrate the mold at a constant angle of gyration during the compaction process. An internal angle of gyration of 20.25 ± 0.35 mrad ($1.16 \pm 0.02^\circ$) as determined by Test Method **D7115** shall be utilized.

NOTE 2—Research has shown external angle (measurement between the external mold wall and the frame of the compactor) to be different from the internal angle (measurement between internal mold wall and top and bottom plate). The difference between these measurements varies for different types of compactors. Some discrepancies in relative density have been resolved by use of the internal angle.

5.1.3 The gyration drive system shall be capable of gyrating the specimen at a rate of 0.5 ± 0.0083 Hz (30.0 ± 0.5 gyrations per minute).

5.1.4 The loading system, ram, and force indicator shall be capable of providing and measuring a constant vertical force to provide an applied pressure of 600 ± 60 kPa during the first five gyrations and 600 ± 18 kPa during the remainder of the compaction process. The applied pressure is defined as the applied force divided by the area of the nominal mold diameter (150 mm).

NOTE 3—The report on the ruggedness evaluation of AASHTO TP4 (T 312)⁶ indicated that the pressure tolerance of ± 18 kPa resulted in significantly different values of bulk specific gravity of the compacted specimens (G_{mb}) in some cases. However, since the pressure is directly set at 600 kPa, the tolerance of ± 18 kPa should apply only to the ability of the SGC to maintain vertical pressure during compaction. To minimize potential errors caused by pressure, operators should take care during verification of calibration to ensure that the specified pressure has been attained.

5.1.5 The axis of the loading ram shall be perpendicular to the platens of the compactor.

5.1.6 The height measurement and recording system shall be capable of continuously measuring and recording the height of the specimen during the compaction process to the nearest 0.1 mm. The height shall be recorded once per gyration.

5.1.7 The system shall record test information such as specimen heights per gyration. This may be accomplished through data acquisition or printing.

5.1.8 The system shall be capable of stopping at a specified number of gyrations or at a specified height through automatic control or operator input.

5.2 *Specimen Molds*—Specimen molds shall have steel walls that are at least 7.5 mm thick and are hardened to Rockwell C48 or better. New molds shall have an inside diameter of 149.90 mm to 150.00 mm. The inside diameter of molds in service shall be 149.90 to 150.20 mm. The inside

⁶ McGennis, R., Kennedy, T. W., Anderson, V. L., Perdomo, D., “The Superpave Gyratory Compactor,” *Journal of the Association of Asphalt Paving Technologists*, Vol 66, 1997, pp. 277–311.