



Designation: D7028 – 07 (Reapproved 2024)

Standard Test Method for Glass Transition Temperature (DMA T_g) of Polymer Matrix Composites by Dynamic Mechanical Analysis (DMA)¹

This standard is issued under the fixed designation D7028; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the procedure for the determination of the dry or wet (moisture conditioned) glass transition temperature (T_g) of polymer matrix composites containing high-modulus, 20 GPa (> 3 × 10⁶ psi), fibers using a dynamic mechanical analyzer (DMA) under flexural oscillation mode, which is a specific subset of the Dynamic Mechanical Analysis (DMA) method.

1.2 The glass transition temperature is dependent upon the physical property measured, the type of measuring apparatus and the experimental parameters used. The glass transition temperature determined by this test method (referred to as “DMA T_g”) may not be the same as that reported by other measurement techniques on the same test specimen.

1.3 This test method is primarily intended for polymer matrix composites reinforced by continuous, oriented, high-modulus fibers. Other materials, such as neat resin, may require non-standard deviations from this test method to achieve meaningful results.

1.4 The values stated in SI units are standard. The values given in parentheses are non-standard mathematical conversions to common units that are provided for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.04 on Lamina and Laminate Test Methods.

Current edition approved Jan. 1, 2024. Originally approved in 2007. Last previous edition approved in 2015 as D7028 – 07^{ε1} (2015). Published January 2024. DOI: 10.1520/D7028-07R24.

2. Referenced Documents

2.1 ASTM Standards:²

D3878 Terminology for Composite Materials

D4065 Practice for Plastics: Dynamic Mechanical Properties: Determination and Report of Procedures

D4092 Terminology for Plastics: Dynamic Mechanical Properties

D5229/D5229M Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases (Withdrawn 2015)³

E1434 Guide for Recording Mechanical Test Data of Fiber-Reinforced Composite Materials in Databases (Withdrawn 2015)³

E1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases (Withdrawn 2015)³

E1640 Test Method for Assignment of the Glass Transition Temperature By Dynamic Mechanical Analysis

E1867 Test Methods for Temperature Calibration of Dynamic Mechanical Analyzers

3. Terminology

3.1 *Definitions*—Terminology D3878 defines terms relating to polymer matrix composites. Terminology D4092 defines terms relating to dynamic mechanical property measurements on polymeric materials.

3.2 *Symbols*: E' = storage modulus

E'' = loss modulus

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

$\tan \delta = E''/E'$ = tangent delta

DMA T_g = glass transition temperature defined from dynamic mechanical analysis measurement

L = length of specimen

W = width of specimen

T = thickness of specimen

T_i = peak temperature from tangent delta curve

4. Summary of Test Method

4.1 A flat rectangular strip of laminate is placed in the DMA equipment and oscillated at a nominal frequency of 1 Hz. The specimen is heated at a rate of 5 °C/min (9 °F/min). The same loading frequency and heating rate is used for both dry and wet specimens (moisture conditioned) to allow for comparison. The temperature at which a significant drop in storage modulus (E') begins is assigned as the glass transition temperature (DMA T_g). The peak temperature of the tangent delta curve (T_i) is identified along with DMA T_g for comparison purposes.

5. Significance and Use

5.1 This test method is designed to determine the glass transition temperature of continuous fiber reinforced polymer composites using the DMA method. The DMA T_g value is frequently used to indicate the upper use temperature of composite materials, as well as for quality control of composite materials.

6. Interferences

6.1 The standard testing machine shall be of the Dynamic Mechanical Analysis (DMA) type of instrument that operates with forced oscillation and applies a flexural loading mode (either three-point bend or dual cantilever) to the test specimen. Refer to Practice D4065 for a summary of various other DMA practices. Other loading modes (such as tensile, torsion or shear) may produce different test results. If another equipment type or loading mode is used the non-standard approach shall be described in the report and the test result recorded as non-standard.

6.2 A fixed frequency of 1 Hz is standard in this test method. In general, for a given material, a higher testing frequency produces a higher DMA T_g value than this standard, while use of the resonance mode will yield a different DMA T_g that may be either higher or lower than the standard. If a non-standard frequency, or the resonance mode, is used, the non-standard approach shall be described in the report and the test result recorded as non-standard.

6.3 A heating rate of 5 °C/min ± 1 °C/min (9 °F/min ± 2 °F/min) is standard in this test method. A change in heating rate will affect the glass transition temperature result; the standard heating rate is the best available compromise for comparing DMA T_g results of dry and wet laminates. If a different heating rate is used it shall be described in the report and the result recorded as non-standard.

NOTE 1—Users should be advised that a heating rate of 5 °C/min represents a compromise between various issues related to T_g measurement precision and bias. It is widely known that heat transfer limitations are more pronounced in DMA apparatus compared to other thermal analysis techniques, such as differential scanning calorimetry (DSC) and

thermomechanical analysis (TMA). For greatest precision, it has been recommended that heating rates be 2 °C/min or less. Test Method E1640 specifies a heating rate of 1 °C/min. However, in many cases 5 °C/min is recommended as a compromise between T_g measurement accuracy and test method convenience, especially for wet laminate measurements, since the slower heating rate will cause specimen drying that will itself bias the results.

6.4 Purge gas type and flow rate and the position of the thermocouple can affect the DMA T_g test result and shall be noted and reported. The same conditions shall be used for both calibration and testing runs. Instrumentation manufacturer recommendations should be followed.

6.5 It is standard in this test method that one of the major fiber directions shall be parallel to the length of the specimen. The span-to-depth ratio, ply orientation, and ply stacking sequence of a specimen with respect to the testing fixture have a profound effect on the DMA T_g result. A meaningful comparison of data requires that the specimen configuration be the same. A non-standard specimen configuration shall be described in the report and the result recorded as non-standard.

6.6 The standard definition in this test method for DMA T_g is based on intersecting two tangent lines from a semi-logarithmic plot of the storage modulus versus temperature. Other T_g definitions typically produce different test results. For example, a linear plot scale will result in a lower value of DMA T_g. A non-standard DMA T_g definition shall be described in the report and the result recorded as non-standard. For comparison purposes the peak temperature of the tangent delta curve (T_i) is identified along with DMA T_g.

7. Apparatus

7.1 *Micrometer*, suitable for reading to 0.025 mm (0.001 in.) accuracy for measuring the specimen thickness and width.

7.2 *Caliper*, suitable for reading to 0.025 mm (0.001 in.) accuracy for measuring the specimen length and instrument clamping distance.

7.3 *Dynamic Mechanical Analyzer (DMA)*, with oven capable of heating to above the glass transition temperature and of controlling the heating rate to the specified value.

8. Sampling and Test Specimens

8.1 Two specimens shall be tested for each sample. If the testing is part of a designed experiment, other sampling techniques may be used if described in the test plan.

8.2 Consult the instrument manufacturer's manual for specimen size. A span-to-thickness ratio greater than ten is recommended. Specimen absolute size is not fixed by this method as various dynamic mechanical analyzers require different sizes. Depending on the analyzer, typical specimen size can range from 56 ± 4 × 12 ± 1 × 2.0 ± 0.5 mm (2.21 ± 0.16 × 0.47 ± 0.04 × 0.08 ± 0.02 in.) (L × W × T) to 22 ± 1 × 3 ± 1 × 1.0 ± 0.5 mm (0.9 ± 0.04 × 0.12 ± 0.04 × 0.04 ± 0.02 in.).

8.3 One of the major fiber directions in the specimen shall be oriented along the length axis of the specimen. It is standard that one of the major fiber directions shall be parallel to the length of the specimen, and specimens containing only off-axis