



Designation: D7522/D7522M – 26

Standard Test Method for Pull-Off Strength for FRP Laminate Systems Bonded to Concrete or Masonry Substrates¹

This standard is issued under the fixed designation D7522/D7522M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method describes the apparatus and procedure for evaluating the pull-off strength of wet lay-up or pultruded (shop-fabricated) Fiber Reinforced Polymer (FRP) laminate systems adhesively bonded to a flat concrete substrate. The test determines the greatest perpendicular force (in tension) that an FRP system can bear before a plug of material is detached. Failure will occur along the weakest plane within the system comprised of the test fixture, FRP laminate, adhesive, and substrate.

1.2 This test method is primarily used for quality control and assessment of field repairs of structures using adhesive-applied composite materials.

1.3 This test method is appropriate for use with FRP systems having any fiber orientation or combination of ply orientations comprising the FRP laminate.

1.4 This test method is appropriate for use with flat concrete, concrete masonry, clay masonry, and stone masonry substrates.

1.5 This test method is not appropriate for use as an “acceptance” or “proof” wherein the FRP system remaining intact at a prescribed force is an acceptable result.

1.6 Pull-off strength measurements depend upon both material and instrumental parameters. Different adhesion test devices and procedures will give different results and cannot be directly compared.

1.7 This test method can be destructive. Spot repairs may be necessary. The test method will result in an exposed cut FRP section; repair methods must consider the potential for moisture uptake through this cut section.

1.8 Prior to the installation of some adhesively bonded FRP systems, the substrate must be patched. This test method is not appropriate for determining the pull-off strength of the FRP

from the patch material. An additional test method is required to determine the pull-off strength of the patch from the substrate.

1.9 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.10 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.11 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [C125 Terminology Relating to Concrete and Concrete Aggregates](#)
- [C1232 Terminology for Masonry](#)
- [D883 Terminology Relating to Plastics](#)
- [D3878 Terminology for Composite Materials](#)
- [D5229/D5229M Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials](#)
- [E6 Terminology Relating to Methods of Mechanical Testing](#)
- [E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process](#)

¹ This test method is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.10 on Composites for Civil Structures.

Current edition approved March 15, 2026. Published April 2026. Originally approved in 2009. Last previous edition approved in 2021 as D7522/D7522M – 21. DOI: 10.1520/D7522_D7522M-26.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



3. Terminology

3.1 *Definitions*—Terminology D3878 defines terms relating to high-modulus fibers and their composites. Terminology D883 defines terms relating to plastics. Terminology E6 defines terms relating to mechanical testing. Terminology C125 defines terms relating to concrete. Terminology C1232 defines terms related to masonry. In the event of a conflict between terms, Terminology D3878 shall have precedence over the other standards.

3.2 Symbols:

D —diameter of the loading fixture.

F_p —pull-off force.

σ_p —pull-off bond stress.

4. Summary of Test Method

4.1 The pull-off test is performed by securing a circular loading fixture (dolly) normal (perpendicular) to the flat surface of the FRP laminate with an affixing adhesive. An adhesion testing device is attached to the loading fixture and aligned to apply tension normal to the test surface. The force applied to the loading fixture is gradually increased and monitored until a plug of material is detached exposing the plane of limiting strength within the system. The nature of the failure is qualified in accordance with the percent of adhesive and cohesive failures, and the actual interfaces and layers involved. The pull-off strength is computed based on the maximum indicated force, the instrument calibration data, and the original surface area stressed. Pull-off strength results using different devices may vary, as results are sensitive to test device parameters.

5. Significance and Use

5.1 The pull-off strength of a bonded FRP system is an important performance property that has been used in specifications, particularly those for assessing the quality of an application. This test method serves as a means for uniformly preparing and testing bonded FRP systems, and evaluating and reporting the results.

5.2 Variations in results obtained using different devices are possible. Therefore, it is recommended that the type of adhesion test device (including manufacturer and model) be mutually agreed upon between the interested parties.

5.3 This test method is intended for use in both the field and the laboratory.

5.4 The basic material properties obtained from this test method can be used in the control of the quality of adhesives and in the theoretical equations for designing FRP systems for external reinforcement to strengthen existing structures.

6. Interferences

6.1 *Material and Specimen Preparation*—Improper preparation of the surface of the composite material before bonding the circular loading fixture is known to cause premature failures at this interface. Improper curing of the bonding adhesive can also cause failure at this interface. Non-uniform FRP or FRP-to-substrate adhesive thickness in one specimen

can affect an individual test result and lead to non-symmetric or mixed-mode failure pattern. Variation in FRP or adhesive thickness between specimens can cause biased or scattered test results. Improper fixturing of the hole cutter relative to the specimen can lead to a non-circular hole or damage to the FRP composite/substrate interface around the perimeter of the hole. This can cause biased or scattered test results and non-symmetric or mixed-mode failure patterns. Misalignment between the circular test fixture and the drilled circle can also lead to biased or scattered test results and non-symmetric or mixed-mode failure patterns.

6.2 *Adhesion Testing Device*—Improper alignment of the adhesion tester grip (see 7.1.3) can lead to biased or scattered test results and non-symmetric or mixed-mode failure patterns. Variation in the rate of loading between specimens can cause biased or scattered test results.

6.3 *Environmental Conditions at Time of Testing*—Testing at non-standard temperature or relative humidity may affect the test results. Specimens tested in field conditions should be noted as such.

6.4 *Location of Test on Masonry Substrate*—Inclusion of a masonry joint within the cut specimen may affect the test results. Tests including a joint should not be used.

7. Apparatus

7.1 *Adhesion Test Device*, commercially available, or comparable apparatus conforming to the following specifications. A specific example of an appropriate commercially available tester is provided in X1.

7.1.1 The tester is comprised of detachable circular loading fixtures, screws with spherical heads that are screwed into the center of a fixture, a socket in the testing assembly that holds the head of the screw, pressure gage or dynamometer, and a mechanical or hydraulic means of applying the force in a controlled manner.

7.1.2 *Loading Fixtures*, having a minimum diameter of 50 mm [2.0 in.], a flat surface on one end that can be adhered to the FRP surface and a means of attachment to the tester on the other end.

7.1.3 *Adhesion Tester Grip*, having a central grip for engaging the loading fixture in a manner such that the resultant force is normal to the FRP surface (typically achieved with a spherical head bearing).

7.1.4 *Adhesion Tester Base*, permitting a uniform bearing against the FRP surface to react the test force.

7.1.5 Means of moving the grip away from the base in as smooth and continuous a manner as possible so that a torsion-free, co-axial (opposing pull of the grip and push of the base along the same axis) force results between them.

7.1.6 *Timer*, or means of limiting the rate of stress applied to the FRP-substrate interface being tested to less than or equal to 1 MPa/min [150 psi/min]. A timer is the minimum equipment when used by the operator along with the force indicator in 7.1.7.

7.1.7 *Force Indicator and Calibration Information*, for determining the actual force delivered to the loading fixture.