



Designation: D7953 – 20 (Reapproved 2024)

Standard Practice for Electrical Leak Location on Exposed Geomembranes Using the Arc Testing Method¹

This standard is issued under the fixed designation D7953; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice is a performance-based standard for an electrical method for locating leaks in exposed geomembranes. For clarity, this practice uses the term “leak” to mean holes, punctures, tears, knife cuts, seam defects, cracks, and similar breaches in an installed geomembrane (as defined in 3.2.6).

1.2 This practice can be used for geomembranes installed in basins, ponds, tanks, ore and waste pads, landfill cells, landfill caps, canals, and other containment facilities. It is applicable for geomembranes made of materials such as polyethylene, polypropylene, polyvinyl chloride, chlorosulfonated polyethylene, bituminous geomembrane, and any other sufficiently electrically insulating materials. This practice is best applicable for locating geomembrane leaks where the proper preparations have been made during the construction of the facility.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D4439 Terminology for Geosynthetics
- D6747 Guide for Selection of Techniques for Electrical Leak Location of Leaks in Geomembranes
- D7002 Practice for Electrical Leak Location on Exposed Geomembranes Using the Water Puddle Method
- D7703 Practice for Electrical Leak Location on Exposed Geomembranes Using the Water Lance Method

3. Terminology

3.1 *Definitions*—For general definitions used in this practice, refer to Terminology D4439.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *artificial leak, n*—an electrical simulation of a leak in a geomembrane.

3.2.2 *conductive-backed geomembrane, n*—a specialty geomembrane manufactured using coextrusion technology featuring an insulating layer in intimate contact with a conductive layer.

3.2.3 *current, n*—the flow of electricity or the flow of electric charge.

3.2.4 *electrical leak location, n*—a method which uses electrical current or electrical potential to locate leaks in a geomembrane.

3.2.5 *electrically isolated conductive-backed geomembrane installation, n*—an installation of conductive-backed geomembrane that achieves a continuously conductive surface on the bottom layer while electrically isolating the bottom conductive layer from the top insulating layer of the entire geomembrane installation.

3.2.6 *leak, n*—for the purposes of this document, a leak is any unintended opening, perforation, breach, slit, tear, puncture, crack, or seam breach. Significant amounts of liquids or solids may or may not flow through a leak. Scratches, gouges, dents, or other aberrations that do not completely

¹ This practice is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.10 on Geomembranes.

Current edition approved Nov. 1, 2024. Published November 2024. Originally approved in 2014. Last previous edition approved in 2020 as D7953 – 20. DOI: 10.1520/D7953-20R24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

penetrate the geomembrane are not considered to be leaks. Types of leaks detected during surveys include but are not limited to: burns, circular holes, linear cuts, seam defects, tears, punctures and material defects.

3.2.7 *poor contact condition, n*—for the purposes of this document, a poor contact condition means that a leak is not in intimate contact with the conductive layer underneath the geomembrane to be tested. This occurs on a wrinkle or wave, under the overlap flap of a fusion weld, in an area of liner bridging and in an area where there is a subgrade depression or rut.

3.2.8 *probe, n*—for the purposes of this document, any conductive rod or conductive brush that is attached to a power source to initiate the arc test.

4. Significance and Use

4.1 Geomembranes are used as barriers to prevent liquids from leaking from landfills, ponds, and other containments. For this purpose, it is desirable that the geomembrane have as little leakage as practical.

4.2 The liquids may contain contaminants that if released can cause damage to the environment. Leaking liquids can erode the subgrade, causing further damage. Leakage can result in product loss or otherwise prevent the installation from performing its intended containment purpose.

4.3 Geomembranes are often assembled in the field, either by unrolling and welding panels of the geomembrane material together in the field, unfolding flexible geomembranes in the field, or a combination of both.

4.4 Geomembrane leaks can be caused by poor quality of the subgrade, poor quality of the material placed on the geomembrane, accidents, poor workmanship, manufacturing defects, and carelessness.

4.5 Electrical leak location methods are an effective and proven quality assurance measure to detect and locate leaks.

5. Summary of Exposed Geomembrane Electrical Location Methods

5.1 *Principles of the Electrical Leak Location Methods for Exposed Geomembranes:*

5.1.1 The principle of the electrical leak location methods is to place a voltage across a geomembrane and then locate areas where electrical current flows through leaks in the geomembrane.

5.1.2 Currently available methods include the water puddle method (Practice D7002), the water lance method (Practice D7703), and the arc testing method.

5.1.3 All of the methods listed in 5.1.2 are effective at locating leaks in exposed geomembranes. Each method has specific site and labor requirements, survey speeds, advantages, and limitations. A professional specializing in the electrical leak location methods can provide guidance on the advantages and disadvantages of each method for a specific project (see Guide D6747).

5.1.4 Alternative ASTM Standard Practices for electrical leak location survey methods should be allowed when mutually agreeable and warranted by adverse site conditions, clearly technical superiority, logistics, or schedule.

6. Arc Testing Method

6.1 A summary of the method capabilities and limitations is presented in Table 1.

NOTE 1—If installed as an electrically isolated conductive-backed geomembrane installation.

6.2 The Principle of the Arc Testing Method:

6.2.1 The principle of this electrical leak location method is to introduce a high voltage between a leak detection test probe and the conductive medium underneath the geomembrane. The area is then swept with a test probe to locate points where the current completes the circuit through a leak. A visible electrical arc is formed when the current completes the circuit and the current flow is also converted into an alarm (audible, visual, or other, which confirms leak detection and location).

6.2.2 Fig. 1 shows a wiring diagram of the arc tester, power supply, and test probe for the arc testing electrical leak location method.

6.3 Leak Location Surveys of Exposed Geomembrane Using the Arc Testing Method:

6.3.1 A grid, test lanes, or other acceptable system should be used to ensure that the entire area is tested with the test probe.

6.3.2 The probe attachment can be different shapes and lengths, depending on the application to be surveyed. The test

TABLE 1 Summary of Arc Testing Method

Geomembranes	Bituminous, CSPE, CPE, EIA, fPP, HDPE, LLDPE, LDPE, PVC, VLDPE	✓	applicable
	Conductive-backed Geomembrane	✓	applicable 1
Seams	All types: welded, tape, adhesive, glued and other	✓	applicable: project specific
Junctions	At synthetic pipes and accessories	✓	applicable: project specific
	At grounded conducting structures	X	not applicable
Survey	During construction phase (installation of GM)	✓	applicable
	After installation (exposed)	✓	applicable
	Slopes	✓	applicable: project specific
	Insufficiently conductive subgrade	X	not applicable
	During the service life (if exposed)	✓	must be generally clean and dry
Climate	Sunny, temperate, warm	✓	applicable
	Rainy weather	X	not applicable
	Frozen conditions	X	not applicable
Leaks detected	Discrimination between multiple leaks	✓	applicable