



Designation: D955 – 21

Standard Test Method of Measuring Shrinkage from Mold Dimensions of Thermoplastics¹

This standard is issued under the fixed designation D955; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method is intended to measure shrinkage from mold cavity to molded dimensions of thermoplastics when molded by compression or injection processes with specified process conditions.

1.2 This test method covers shrinkage measurements at 24 and 48 hours.

1.3 This method will give comparable data based on standard specimens and can not predict absolute values in actual molded parts with varying flow paths, wall thicknesses, pressure and temperature gradients and process conditions. Differences in mold shrinkage may also be observed among the three specimen geometries described in this test method.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are given for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—This standard and ISO 294-3 are equivalent in the design of specimen D2. This test method is equivalent to ISO 294-4 where Type D2 specimens and the procedure in [Appendix X2](#) are used.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.09](#) on Specimen Preparation. Current edition approved April 1, 2021. Published April 2021. Originally approved in 1948. Last previous edition approved in 2014 as D955 - 08(2014). DOI: 10.1520/D0955-21.

2. Referenced Documents

2.1 ASTM Standards:²

- [D618 Practice for Conditioning Plastics for Testing](#)
 - [D788 Classification System for Poly\(Methyl Methacrylate\) \(PMMA\) Molding and Extrusion Compounds](#)
 - [D883 Terminology Relating to Plastics](#)
 - [D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials](#)
 - [D4066 Classification System for Nylon Injection and Extrusion Materials \(PA\)](#)
 - [D4549 Classification System and Basis for Specification for Polystyrene and Rubber-Modified Polystyrene Molding and Extrusion Materials \(PS\)](#)
 - [D4703 Practice for Compression Molding Thermoplastic Materials into Test Specimens, Plaques, or Sheets](#)
 - [D4976 Specification for Polyethylene Plastics Molding and Extrusion Materials](#)
 - [D5947 Test Methods for Physical Dimensions of Solid Plastics Specimens](#)
 - [D6778 Classification System and Basis for Specification for Polyoxymethylene Molding and Extrusion Materials \(POM\)](#)
 - [D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials \(PA\)](#)
 - [E456 Terminology Relating to Quality and Statistics](#)
 - [E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)
 - [E2935 Practice for Conducting Equivalence Tests for Comparing Testing Processes](#)
- ### 2.2 ISO Standards:³
- [ISO 293 Plastics—Compression Moulding Test Specimens of Thermoplastic Materials](#)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

ISO 294-1 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 1: General Principles, and Moulding of Multipurpose and Bar Test specimens

ISO 294-3 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 3: Small Plates

ISO 294-4 Plastics—Injection Moulding of Test Specimens—Part 4: Determination of Moulding Shrinkage

3. Terminology

3.1 *Definitions*—Terms used in this standard are defined in accordance with Terminology D883, unless otherwise specified. For terms relating to precision and bias and associated issues, the terms used in this standard are defined in accordance with Terminology E456.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *jetting, n*—non-uniform multi-directional flow front apparent on the surface of the mold due to rapid filling of the mold cavity.

4. Summary of Test Method

4.1 The principle of this test method is to compare mold cavity dimensions with specimen dimensions and report the differences in percent.

5. Significance and Use

5.1 *Injection Molding*—In injection molding, the difference between the dimensions of a mold cavity and of the molded specimen may vary according to the design of the mold and operation of the molding process. Factors such as mold and

melt temperature, fill times, and packing conditions are known to affect shrinkage significantly. Adherence to the specified mold design (see 7.1) and specifications outlined in Practice D3641 or ISO 294-4 or the appropriate material specification will improve the reproducibility of the test.


5.2 *Compression Molding*—In compression molding, the difference between the dimensions of a mold cavity and of the molded specimen may vary according to the design of the mold and operation of the molding process. Factors, such as the amount of material in charge, cooling time, and pressure application are known to affect shrinkage significantly. Adherence to the specified mold design (see 7.2) and specifications outlined in Practice D4703 or ISO 293 or the appropriate material specifications will improve the reproducibility of the test.

6. Sample Preparation

6.1 Some materials require special treatment before they are molded. For example, thermoplastics, which absorb moisture must be dried before molding. For required conditions for sample preparation, refer to the appropriate material specification or the manufacturer's recommendations if no specification is available. The preparation given to the material prior to molding shall be recorded and reported.

7. Apparatus

7.1 *Injection Mold*—Specimens shall be molded in a two cavity mold conforming with dimensions as shown in Figs. 1 and 2 for the 60 × 60-mm plaque specimen (Type D2), Fig. 3 for the 12.7 by 127-mm bar specimen (Type A) and Fig. 4 for



Sp | sprue

G | gate

L_c = distance between the lines along which the test specimens are cut from the runners

Molding volume = 20 000 mm³

Projected area = 11 000 mm²

FIG. 1 Type D2 (Mold Layout)