



Designation: E1358 – 24

Standard Test Method for Determination of Moisture Content of Particulate Wood Fuels Using a Microwave Oven¹

This standard is issued under the fixed designation E1358; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method provides an alternative method to Test Method E871, for the determination of the moisture of particulate wood fuels. Particulate wood fuels are defined in Terminology E1126.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E871 Test Method for Moisture Analysis of Particulate Wood Fuels

E1126 Terminology Relating to Biomass Fuels (Withdrawn 2003)³

E1705 Terminology Relating to Bioenergy and Industrial Chemicals from Biomass

3. Terminology

3.1 *Definitions of Terms:*

¹ This test method is under the jurisdiction of ASTM Committee E48 on Bioenergy and Industrial Chemicals from Biomass and is the direct responsibility of Subcommittee E48.05 on Biomass Conversion.

Current edition approved May 1, 2024. Published August 2024. Originally approved in 1990. Last previous edition approved in 2019 as E1358 – 97 (2019). DOI: 10.1520/E1358-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3.1.1 For definitions of terms used in this standard, refer to Terminology E1705.

NOTE 1—The user is advised that the definitions used by various industries, marketers, regulatory bodies, and other ASTM Committees can differ from those in this standard. When using this standard, it is critical to use terminology from Committee E48.

4. Summary of Test Method

4.1 Moisture is determined by establishing the loss in mass of the sample when heated under rigidly controlled conditions of temperature, time, sample mass, and equipment specifications.⁴

5. Significance and Use

5.1 This test method provides a rapid determination for moisture in particulate wood fuels in several minutes. The standard method, Test Method E871, requires a minimum of 18 h. This method is applicable to situations such as the spot-check of the moisture delivered by truck where a quick indication of the moisture of wood delivered is desirable.

6. Apparatus

6.1 *Microwave Oven*—Any standard commercial microwave oven having a power output of at least 600 W can be used.

7. Procedure

7.1 Obtain a 50 g sample of the wood to be tested using techniques outlined in Test Method E871.

7.2 Determine the weight of 3 sheets of standard paper towels placed on top of each other. Record this mass as M_T (Mass of Towels).

7.3 Place the 50 g sample of the wood on top of the paper towels and determine the mass of the initial sample. Record the mass as M_{STI} (Mass of Sample and Towels Initial).

7.4 Place the sample in the microwave and heat on full power using the schedule shown in Table 1 for the type of

⁴ Harris, R. A., "Rapid Determination of Wood Fuel Moisture Using a Microwave Oven for Drying," *Forest Products Journal*, Vol 32, No. 10, October 1982, pp. 56–59.