



Designation: E1558 – 09 (Reapproved 2021)

Standard Guide for Electrolytic Polishing of Metallographic Specimens¹

This standard is issued under the fixed designation E1558; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide deals with electrolytic polishing as a means of preparation of specimens for metallographic purposes. Procedures are described for polishing a variety of metals.

NOTE 1—References (1-133)² on electrolytic polishing will provide the reader with specific information beyond the scope of this guide.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific safety precautions are described in Section 5 and 6.3.1.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

E7 Terminology Relating to Metallography

E407 Practice for Microetching Metals and Alloys

3. Terminology

3.1 *Definitions*—All terms used in this guide are either defined in Terminology E7 or are discussed in 3.2.

3.2 *Definitions of Terms Specific to This Standard:*

¹ This guide is under the jurisdiction of ASTM Committee E04 on Metallography and is the direct responsibility of Subcommittee E04.01 on Specimen Preparation. Current edition approved Sept. 1, 2021. Published November 2021. Originally approved in 1993. Last previous edition approved in 2014 as E1558 – 09(2014). DOI: 10.1520/E1558-09R21.

² The **boldface** numbers in parentheses refer to the references at the end of this standard.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.1 *electrolytic polish (electropolish)*—A method of polishing metals and alloys in which material is removed from the surface by making the metal the anode in an electrolytic bath.

4. Significance and Use

4.1 *Advantages of Electrolytic Polishing:*

4.1.1 For some metals, a high quality surface finish can be produced that is equivalent to, or better than, that which can be obtained by mechanical methods.

4.1.2 Once procedures have been established, satisfactory results can be obtained rapidly with reproducibility.

4.1.3 There can be a marked saving of time if many specimens of the same material are polished sequentially.

4.1.4 Electropolishing a selected area on the surface of a relatively large metal part can be accomplished nondestructively, that is, without the need for sectioning to remove a piece.

4.1.5 Soft, single-phase metals, which may be difficult to polish by mechanical methods, may be successfully electropolished.

4.1.6 The true microstructure of a specimen can be obtained because artifacts (such as disturbed metal, scratches, and mechanical twins) produced on the surface, even by careful grinding and mechanical polishing operations, can be removed. These features are important in low-load hardness testing, X-ray diffraction studies, and in electron microscopy, where higher resolution puts a premium on undistorted metal surfaces.

4.1.7 After electropolishing is completed, etching can often be accomplished by reducing the voltage (generally to about one-tenth that required for polishing) for a short time before it is turned off.

NOTE 2—Not all electropolishing solutions produce good etching results.

4.2 *Disadvantages of Electrolytic Polishing:*

4.2.1 Many of the chemical mixtures used in electropolishing are poisonous or dangerous if not properly handled (see Section 5). These hazards are similar to those involved in the mixing and handling of etchants, see Test Methods E407.

4.2.2 In multi-phase alloys, the polishing rate of each phase may be different. The result may be a non-planar surface.

4.2.3 Electropolished surfaces may be slightly undulated rather than perfectly planar and, therefore, may not be suitable for examination at all magnifications.

4.2.4 The rate of polishing in areas adjacent to various inhomogeneities, such as nonmetallic inclusions and voids, is usually greater than that in the surrounding matrix and tends to exaggerate the size of the inclusions and voids.

4.2.5 Dimples, pits, and waviness limit applications involving surface phenomena, coatings, interfaces, and cracks. Edges tend to be attacked preferentially, resulting in edge rounding.

4.2.6 Artifacts may be produced by electropolishing.

4.2.7 Specimen mounting materials may react with the electrolyte.

4.2.8 The electropolished surfaces of certain materials may be passive and difficult to etch.

4.2.9 Metal removal rates by electropolishing are usually quite low, typically about 1 $\mu\text{m}/\text{min}$, and all of the prior induced damage from cutting and grinding may not be removed if preparation is stopped after a 600-grit SiC grind and electropolishing times are short.

4.2.10 A large number of electrolytes may be needed to polish the variety of metals encountered by a given laboratory. Considerable time may be required to develop a procedure for a new alloy.

5. General Safety Precautions

5.1 Before using or mixing any chemicals, all product labels and pertinent Material Safety Data Sheets (MSDS) should be read and understood concerning all of the hazards and safety precautions to be observed. Users should be aware of the type of hazards involved in the use of all chemicals used, including those hazards that are immediate, long-term, visible, invisible, and with or without odors.

5.1.1 Consult the product labels and MSDS for recommendations concerning proper protective clothing.

5.1.2 All chemicals are potentially dangerous. All persons using any electrolyte should be thoroughly familiar with all of the chemicals involved and the proper procedure for handling, mixing, and disposing of each chemical, as well as any combinations of those chemicals.

5.1.3 When pouring, mixing, or etching, always use the proper protective equipment (glasses, gloves, apron, etc.) and it is strongly recommended to always work under a certified and tested fume hood. This is imperative with etchants that give off noxious odors or toxic vapors. In particular, note that solutions containing perchloric acid must be mixed and used in an exclusive hood equipped with a wash down feature to avoid accumulation of explosive perchlorates.

5.1.4 **Table 1** includes specific safety precautions for the mixing or use of some electrolytes. The user should take care to observe each of these specific precautions.

5.2 Some basic suggestions for the handling and disposal of electrolytes and their ingredients are as follows:

5.2.1 As previously stated, it is good practice to always work under a certified fume hood when mixing and utilizing any electrolyte and it is imperative with those electrolytes that give off noxious odors or toxic vapor. Additionally, the electrolytes in Groups I and II must be treated with extra caution because dried perchlorates can accumulate in hood ductwork and on work surfaces creating the potential for a powerful accidental explosion. Therefore, these electrolytes

must only be used in an exclusive hood equipped with a wash down feature. To avoid the accumulation of explosive, dry perchlorates, the hood should undergo a wash down cycle following each use.

5.2.2 When pouring, mixing, or using electrolytes, always use the proper protective equipment (eyewear, gloves, apron, and so forth).

5.2.3 Use proper devices (glass or plastic) for weighing, measuring, mixing, containing, and storage of solutions.

5.2.4 When mixing electrolytes, always add reagents to the solvent unless specific instructions indicate otherwise.

5.2.5 When using an electrolyte, always avoid direct physical contact with the electrolyte and the specimen. Use tongs or some other indirect method of handling specimens.

5.2.6 Methanol is a cumulative poison hazard. Where ethanol or methanol are listed as alternates, ethanol is the preferred solvent. Methanol should be used in a properly designed chemical fume hood.

5.2.7 All spills should be cleaned up and disposed of properly, no matter how small the spill.

5.2.8 Properly dispose of all solutions that are not identified by composition and concentration.

5.2.9 Store, handle, and dispose of chemicals according to the manufacturer's recommendations. Observe printed cautions on reagent containers.

5.2.10 Information pertaining to the toxicity hazards and working precautions of chemicals, solvents, acids, bases, and so forth, being used (such as MSDS) should be available for rapid consultation.

5.3 Many of the electrolytes in the following listing can be exceedingly dangerous if carelessly handled. The pertinent safety precautions for each class of electrolyte should be read before any electrolyte is mixed or used.

5.4 Electrolytes containing perchloric acid and acetic anhydride are very dangerous to mix and may be unpredictable in use. Many industrial firms and research laboratories forbid the use of such mixtures. Certain cities also have ordinances prohibiting the use of such potentially explosive mixtures. These facts are considered sufficient reason for recommending against their use.

5.5 Mixtures of oxidizable organic compounds and powerful oxidizing agents are always potentially dangerous. After some use, any electrolyte will become heavily laden with ions of the metals polished. These ions may interfere with further polishing or catalyze the decomposition of the electrolyte. The electrolyte then must be discarded in accordance with appropriate regulations.

5.6 Most electrolytes (with few exceptions) should be mixed and stored in clean glass containers and never be in contact with foreign materials or organic compounds. The exceptions are those electrolytes containing fluorides and strong alkaline solutions that should be mixed and stored in polyethylene or other appropriate material containers. Electrolytes must never be allowed to become concentrated by evaporation. All electrolytes should be discarded appropriately as soon as they have exceeded their immediate usefulness.