



Designation: E2602 – 22

Standard Test Methods for Assignment of the Glass Transition Temperature by Modulated Temperature Differential Scanning Calorimetry¹

This standard is issued under the fixed designation E2602; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods describe the assignment of the glass transition temperature of materials using modulated temperature differential scanning calorimetry (MTDSC) over the temperature range from -120°C to $+600^{\circ}\text{C}$. The temperature range may be extended depending upon the instrumentation used.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E473 Terminology Relating to Thermal Analysis and Rheology

E967 Test Method for Temperature Calibration of Differential Scanning Calorimeters and Differential Thermal Analyzers

E968 Practice for Heat Flow Calibration of Differential Scanning Calorimeters

E1142 Terminology Relating to Thermophysical Properties

¹ These test methods are under the jurisdiction of ASTM Committee E37 on Thermal Measurements and is the direct responsibility of Subcommittee E37.01 on Calorimetry and Mass Loss.

Current edition approved Feb. 1, 2022. Published May 2022. Originally approved in 2009. Last previous edition approved in 2015 as E2602 – 09 (2015). DOI: 10.1520/E2602-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E1356 Test Method for Assignment of the Glass Transition Temperatures by Differential Scanning Calorimetry

E1545 Test Method for Assignment of the Glass Transition Temperature by Thermomechanical Analysis

E1640 Test Method for Assignment of the Glass Transition Temperature By Dynamic Mechanical Analysis

3. Terminology

3.1 *Definitions*—Specific technical terms found in these test methods are defined in Terminologies E473 and E1142 including *differential scanning calorimetry*, *extrapolated onset*, *glass transition*, *glass transition temperature*, *non-reversing*, *reversing*, *specific heat capacity*, and *thermal curve*.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *extrapolated end temperature (T_e)*, n —the point of intersection of the tangent drawn at the point of greatest slope (that is, the inflection point) in the transition region with the extrapolated baseline following the transition.

3.2.2 *extrapolated onset temperature (T_f)*, n —the point of intersection of the tangent drawn at the point of greatest slope (that is, the inflection point) in the transition region with the extrapolated baseline prior to the transition.

3.2.3 *midpoint temperature (T_m)*, n —the point on the thermal curve corresponding to the average of the extrapolated onset and extrapolated end temperatures.

3.2.4 *modulated*, n —a prefix indicating that a parameter changes in a periodic manner during the experiment.

3.2.5 *modulated heat flow*, n —the heat flow resulting from an applied modulated temperature program.

3.2.6 *modulated temperature differential scanning calorimetry (MTDSC)*, n —a method of differential scanning calorimetry (DSC) that varies the temperature sinusoidally or with a periodic step-and-hold or pulse program to the test specimen over a traditional isothermal or temperature ramp program. Results from the experiment include reversing and nonreversing heat flow and specimen temperature.

3.2.7 *total heat flow*, n —the value of the modulated heat flow averaged over one modulation period or impulse.

3.2.7.1 *Discussion*—The total heat flow is equivalent to the heat flow signal of conventional differential scanning calorimetry.

3.2.7.2 *Discussion*—The total heat flow is equal to the sum of the reversing and nonreversing heat flows.

4. Summary of Test Method

4.1 The determination of the glass transition by differential scanning calorimetry using Test Method E1356 is difficult when kinetic events such as the cure exotherm of a thermoset resin occur at or near the glass transition. In MTDSC, the total heat flow signal is separated into reversing and nonreversing components. The heat capacity change that indicates the glass transition appears in the reversing heat flow signal, while kinetic events (for example, curing, enthalpy of recovery, etc.) appear in the nonreversing heat flow signal. The separation of these two signals permits the determination of the enthalpy of reaction and the assignment of the glass transition in a single experiment.

4.1.1 This MTDSC method involves the continuous monitoring of the reversing and nonreversing heat flow into or out of a test specimen as it is heated at a controlled rate through the glass transition region.

5. Significance and Use

5.1 Materials undergo an increase in molecular mobility at the glass transition seen as a sigmoidal step increase in the heat capacity. This mobility increase may lead to kinetic events such as enthalpic recovery, chemical reaction or crystallization at temperatures near the glass transition. The heat flow associated with the kinetic events may interfere with the determination of the glass transition.

5.2 The glass transition is observed in differential scanning calorimetry as a sigmoidal or step change in specific heat capacity.

5.3 MTDSC provides a test method for the separation of the heat flow due to heat capacity and that associated with kinetic events making it possible to determine the glass transition in the presence of interfering kinetic event.

5.4 These test methods are useful in research and development, quality assurance and control and specification acceptance.

5.5 Other methods for assigning the glass transition temperature include differential scanning calorimetry (Test Method E1356), thermomechanical analysis (Test Method E1545) and dynamic mechanical analysis (Test Method E1640).

6. Apparatus

6.1 The instrumentation required to provide the capability for these test methods includes a MTDSC composed of:

6.1.1 A *differential scanning calorimeter (DSC) test chamber* of (1) a furnace or furnaces to provide uniform controlled heating or cooling of a specimen and reference to a constant temperature or at a constant rate within the range from -120°C to $+600^{\circ}\text{C}$, (2) a temperature sensor to provide an indication of the specimen temperature readable to $\pm 0.02^{\circ}\text{C}$, (3) a differential sensor to detect a heat flow difference between specimen and reference equivalent to $1\ \mu\text{W}$ and (4) a means of sustaining a test chamber environment of inert nitrogen (or

other low conductivity) purge gas at a rate of 20 mL/min to 60 mL/min constant to within $\pm 10\%$.

NOTE 1—The temperature range of interest depends upon the temperature of the glass transition. The apparatus need only address the temperature region from 50°C below to 50°C above the anticipated glass transition temperature.

6.1.2 A *temperature controller*, capable of executing a specific temperature program by (1) operating the furnace between selected temperature limits at a rate of temperature change of $7^{\circ}\text{C}/\text{min} \pm 0.1^{\circ}\text{C}/\text{min}$, (2) holding at an isothermal temperature within the temperature range of -120°C to $+600^{\circ}\text{C}$ within $\pm 0.1^{\circ}\text{C}$, and (3) for Test Method A, varying temperature sinusoidally with an amplitude of $\pm 0.9^{\circ}\text{C}$ to 1.1°C and a period of 50 s to 71 s (frequency of 14 mHz to 20 mHz) or applying a $\pm 0.5^{\circ}\text{C}$ pulse at intervals between 15 s and 30 s.

6.1.3 A *calculating device*, capable of transforming the experimentally determined modulated temperature and modulated specimen heat flow signals into the required continuous output forms of reversing and nonreversing heat flow and average test temperature to the required accuracy and precision.

6.1.4 A *data collection device*, to provide a means of acquiring, storing and displaying measured or calculated signals or both. The minimum output signals required for MTDSC are heat flow, reversing heat flow, nonreversing heat flow, elapsed time and average specimen temperature signals.

6.2 A *coolant system* to provide cooling at rates of at least $2^{\circ}\text{C}/\text{min}$.

6.3 *Inert nitrogen* or other low conductivity purge gas flowing at a rate of 20 mL/min to 60 mL/min constant to within $\pm 10\%$.

NOTE 2—Helium, a commonly used purge gas with high thermal conductivity, may result in reduced temperature range, precision and accuracy. Follow the manufacturers recommendation when using helium.

6.4 A *balance* with a range of at least 200 mg to weigh specimens or containers, or both to $\pm 0.01\text{ mg}$.

6.5 A *Sapphire disk calibration material*, 10 mg to 30 mg for heat capacity calibration.

6.6 *Indium metal* of $>99.99\%$ purity for temperature and enthalpy calibration.

6.7 *Containers* (pans, crucibles, etc.) that are inert to the specimen and are of suitable structural shape and integrity to contain the specimen in accordance with the specific requirements of these test methods.

6.8 A means, tool or device to close, encapsulate or seal the container of choice.

7. Calibration and Standardization

7.1 Calibrate the temperature signal from the MTDSC apparatus in accordance with Practice E967 using an indium reference material and a heating rate of $5^{\circ}\text{C}/\text{min}$ (see Note 3 and Note 5).

7.2 If the manufacturer requires, calibrate the total heat flow signal from the MTDSC apparatus in accordance with Practice E968 using an indium reference material.