



Designation: E3165 – 18 (Reapproved 2025)

Standard Test Method for Nighttime Retroreflected Chromaticity of Retroreflective Sheeting¹

This standard is issued under the fixed designation E3165; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes the instrumental determination of the nighttime retroreflected chromaticity coordinates of retroreflective sheeting.

1.2 This method includes a procedure based on tristimulus filter colorimetry and a procedure based on spectral measurements.

1.3 A single set of test geometries (using 0.33° observation angle and 5° entrance angle) and apertures are described in this method.

1.4 The resulting chromaticity coordinates are for use with the CIE 1931 chromaticity system utilizing CIE Illuminant A.

1.5 If measurements and calculations are required for other sources of illumination, or geometries, or other materials, the user is referred to the general practice described in Practice E811.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.10 on Retroreflection.

Current edition approved Nov. 1, 2025. Published December 2025. Originally approved in 2018. Last previous edition approved in 2018 as E3165 – 18. DOI: 10.1520/E3165-18R25.

2. Referenced Documents

2.1 ASTM Standards:²

D4956 Specification for Retroreflective Sheeting for Traffic Control

E284 Terminology of Appearance

E308 Practice for Computing the Colors of Objects by Using the CIE System

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E808 Practice for Describing Retroreflection

E809 Practice for Measuring Photometric Characteristics of Retroreflectors

E810 Test Method for Coefficient of Retroreflection of Retroreflective Sheeting Utilizing the Coplanar Geometry

E811 Practice for Measuring Colorimetric Characteristics of Retroreflectors Under Nighttime Conditions

2.2 CIE and ISO Documents:³

CIE Publication 15:2004 Colorimetry

CIE Technical Report 54.2 Retroreflection: Definition and Measurement

CIE Technical Report 72 Guide to the Properties and Uses of Retroreflectors at Night

ISO 11664-1:2007 (CIE S 014-1/E:2006) Colorimetry—Part 1: CIE Standard Colorimetric Observers

ISO 11664-2:2007 (CIE S 014-2/E:2006) Colorimetry—Part 2: CIE Standard Illuminants

2.3 U. S. Federal Regulations:⁴

US Code of Federal Regulations (CFR) Title 23: Highways: Part 655—Traffic Operations, Subpart F—Traffic Control

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from U.S. National Committee of the CIE (International Commission on Illumination), C/o Alan Laird Lewis, 282 E. Riding, Carlisle, MA 01741, <http://www.cie-usnc.org>.

⁴ Available from U.S. Government Printing Office, Superintendent of Documents, 732 N. Capitol St., NW, Washington, DC 20401-0001, <http://www.access.gpo.gov>.

3. Terminology

3.1 The terms and definitions in Terminology E284 apply to this test method.

3.2 Definitions:

3.2.1 *chromaticity coordinates*, n —the ratio of each of the tristimulus values of any viewed light to the sum of the three.

3.2.1.1 *Discussion*—Chromaticity coordinates in the CIE 1931 system of color specification are designated by x , y , and z .

3.2.2 *spectral coefficient of retroreflection* $R_A(\lambda)$, n —the ratio of the spectral coefficient of radiant intensity $R_I(\lambda)$ of the retroreflector for a given geometrical configuration to the area A of the retroreflector.

$$R_A(\lambda) = \frac{R_I(\lambda)}{A}$$

3.2.3 *spectral coefficient of retroreflected radiant intensity* $R_I(\lambda)$, n —the ratio of the spectral radiant intensity $I_e(\lambda)$ of the retroreflector for a given geometrical configuration to the spectral irradiance $E_e(\lambda)$ of the incident light source at the retroreflector on a plane perpendicular to the illumination axis.

$$R_I(\lambda) = \frac{I_e(\lambda)}{E_{e\perp}(\lambda)}$$

4. Summary of Test Method

4.1 The general procedure is to illuminate the test specimen with the specified source, in the prescribed geometry, and analyze the reflected light using the calculation in DIE Publication 15.

4.2 The geometric arrangement can be either a longer-distance photometric range or an optically-reduced equivalent geometry for laboratory bench or field work.

4.3 The measurements may be performed using a substitution standard calibrated by an appropriate calibration laboratory. Measurements are then relative to this standard.

5. Significance and Use

5.1 The results of this test method are used to assess conformance of retroreflective sheeting to the nighttime color requirements of industry standards and government regulations, such as Specification D4956 and U.S. Code of Federal Regulations Title 23 Part 655 Subpart F.

5.2 Requirements in specifications referring to this test method are for the chromaticity of the material as viewed at night. These requirements are generally stated using four or five corner points that form a box that limits the range of acceptable chromaticity. Most of these specifications are categorical in nature; they describe a small range of colors that are recognizable from a color naming or coding purpose.

5.3 The method for compliance with the specification is to plot the measured (x , y) values and determine if the measured point falls within the specification box for the color of interest.

6. Apparatus

6.1 The apparatus consists of a light source, a receptor (tristimulus or spectral) and the geometric arrangement (either in a photometric range or an optically-reduced design for laboratory bench or field use).

6.2 The light source shall closely approximate the spectral distribution of CIE Illuminant A (a correlated color temperature of 2856 K, see Practice E308).

NOTE 1—Non-fluorescent samples may be illuminated with non-Illuminant A (for example, broadband) light sources using this method. The CIE Illuminant A light source is considered the referee condition for this test method.

6.3 The receptor shall closely approximate the CIE tristimulus functions when used. For spectral testing the dispersing elements shall provide a range from 380 nm to 740 nm with a 5 nm increment and a 5 nm bandpass. (For spectral measurements made by systems with increment and bandpass ≤ 5 nm, for example, array detectors, integration techniques are acceptable to obtain the equivalent of a 5 nm bandpass).

NOTE 2—Other bandpass specifications may be used. For example, the precision and bias data contained in Section 12 were collected by equipment having either 5 nm or 10 nm bandpass. The 5 nm bandpass is considered the referee condition for this test method.

7. Sampling, Test Specimens, and Test Units

7.1 Multiple samples shall be gathered from the retroreflective sheeting material in a manner so as to constitute a representative sampling. One example of a sampling procedure is described in Section 9 of Specification D4956. Deviations from this procedure shall be described in the report.

7.2 The reference test specimen in this procedure shall be 200 mm $\pm$ 100 mm by 200 mm $\pm$ 100 mm in size. The entire specimen to be measured shall be illuminated.

NOTE 3—The sample dimensions specified above refer to the referee laboratory measurement. Field measurements may dictate other sample dimension requirements. In all cases, the minimum illuminated area shall be a circle having a 25 mm diameter.

7.3 Retroreflective sheeting materials may have color characteristics that vary slowly with changes in observation, entrance, and orientation angle. Care should be taken to ensure careful preparation of the sample and placement in the measurement system.

7.4 Retroreflective sheeting may produce small “rainbow like” diffraction effects at some observation angles. If there is concern that these effects are present, then the maximum fixed aperture size (10 min of arc; see 9.2) is to be used as the referee configuration. In general, measurements at apertures less than the maximum size will provide no significant effect on the results and may be used.

7.5 *Measurement Angles*—This method uses the CIE goniometer system (α , β_1 , β_2 , ϵ). The angles used in the measurement are: observation angle $\alpha = 20$ min of arc (0.33°), entrance angle $\beta_1 = 5^\circ$, entrance angle $\beta_2 = 0^\circ$, and rotation angles ϵ of 0° and 90° .

8. Calibration and Standardization

8.1 Calibration of these instruments is to be performed relative to a known spectral or tristimulus standard from a reliable source.