



Designation: F1506 – 22

Standard Performance Specification for Flame Resistant and Electric Arc Rated Protective Clothing Worn by Workers Exposed to Flames and Electric Arcs¹

This standard is issued under the fixed designation F1506; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification identifies minimum performance requirements to determine the (a) arc rating of fabrics, (b) flame resistance of fabrics and subassemblies, (c) mechanical durability of the fabrics and subassemblies, (d) the minimum garment construction and performance requirements, and (e) the garment labeling requirements for the completed protective clothing worn by workers exposed to flames and electric arcs.

1.1.1 The minimum requirements for garment labeling are intended to provide end users with adequate information to select garments with the appropriate arc rating.

1.1.2 End users are required to perform an assessment to determine the level of hazard and the required arc rating of the protective clothing for their individual hazards.

1.1.2.1 The end user risk assessments are outside the scope of this standard.

1.2 This performance specification does not address coated or laminated protective clothing commonly used for rainwear applications in an arc hazard environment. Performance requirements related to this category of protective clothing are detailed in Specification **F1891**.

1.3 This performance specification does not address hand protection. Performance and test requirements related to hand protection are detailed in OSHA 1910.138, Specification **D120**, and Test Method **F2675/F2675M**.

1.4 The care and maintenance requirements for laundering electric arc flash protective clothing are outside the scope of this standard. Refer to Guides **F1449** or **F2757** related to industrial or home laundering.

1.5 *This standard should be used to evaluate and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions. It*

should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions.

1.5.1 The results of this evaluation may be used as elements of a fire-risk assessment that takes into account all of the factors that are pertinent to an assessment of the fire hazard of a particular end use.

1.6 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.7 The following precautionary caveat pertains only to the test methods portion, Section 7, of this performance specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D120 Specification for Rubber Insulating Gloves

D123 Terminology Relating to Textiles

D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus

D1776/D1776M Practice for Conditioning and Testing Textiles

D2261 Test Method for Tearing Strength of Fabrics by the Tongue (Single Rip) Procedure (Constant-Rate-of-Extension Tensile Testing Machine)

D2724 Test Method for Bond Strength of Bonded, Fused, and Laminated Apparel Fabrics

¹ This performance specification is under the jurisdiction of ASTM Committee **F18** on Electrical Protective Equipment for Workers and is the direct responsibility of Subcommittee **F18.65** on Wearing Apparel.

Current edition approved March 1, 2022. Published April 2022. Originally approved in 1994. Last previous edition approved in 2020 as F1506–20a. DOI: 10.1520/F1506-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D3776/D3776M Test Methods for Mass Per Unit Area (Weight) of Fabric

D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method

D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

D6413 Test Method for Flame Resistance of Textiles (Vertical Test)

D7138 Test Method to Determine Melting Temperature of Synthetic Fibers

F1449 Guide for Industrial Laundering Care and Maintenance of Flame Resistant or Arc Rated Clothing

F1891 Specification for Arc and Flame Resistant Rainwear

F1959/F1959M Test Method for Determining the Arc Rating of Materials for Clothing

F2178 Specification for Arc Rated Eye or Face Protective Products

F2675/F2675M Test Method for Determining Arc Ratings of Hand Protective Products Developed and Used for Electrical Arc Flash Protection

F2757 Guide for Home Laundering Care and Maintenance of Flame Resistant or Arc Rated Clothing

F2894 Test Method for Evaluation of Materials, Protective Clothing, and Equipment for Heat Resistance Using a Hot Air Circulating Oven

2.2 AATCC Test Methods:³

Method 61 Colorfastness to Washing, Domestic and Laundering, Commercial: Accelerated

Method 132 Colorfastness to Dry-Cleaning

Method 135 Dimensional Changes Automatic Home Laundering of Woven and Knitted Fabrics

Method 158 Dimensional Changes on Drycleaning in Perchloroethylene: Machine Method

2.3 ANSI/ISEA Standards:⁴

107-2015 American National Standard for High-Visibility Safety Apparel and Accessories

125-2014 American National Standard for Conformity Assessment of Safety and Personal Protective Equipment

2.4 CSA Standard:⁵

CSA Z96 High-Visibility Safety Apparel

2.5 Federal Standards:

29 CFR 1910.138 Hand Protection⁶

2.6 ISO Standards:⁷

ISO 9001 Quality management systems — Requirements

ISO/IEC 17025 General requirements for the competence of testing and calibration laboratories

ISO/IEC 17065 Conformity assessment — Requirements for bodies certifying products, processes and services

ISO 20471 High visibility clothing — Test methods and requirements

2.7 NFPA Standard:⁸

NFPA 2112 Standard on Flame-Resistant Clothing for Protection of Industrial Personnel Against Short-Duration Thermal Exposures from Fire

3. Terminology

3.1 Definitions—For definitions of textile terms used in this performance specification, refer to Terminology **D123**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 afterflame, *n*—persistent flaming of a material after the ignition source has been removed.

3.2.1.1 Discussion—In arc testing, a visible flaming on or near a test specimen which persists after the arc exposure has ended. The afterflame ceases when flaming is no longer visible.

3.2.2 afterflame time, *n*—the length of time for which a material continues to flame after the ignition source has been removed.

3.2.2.1 Discussion—In arc testing, the length of time for which a specimen continues to exhibit visible flaming as determined by a time display video recording of the specimen during arc testing.

3.2.3 arc rating, *n*—value attributed to materials that describes their performance to exposure to an electrical arc discharge.

3.2.3.1 Discussion—The arc rating is expressed in cal/cm² and is derived from the determined value of ATPV or E_{BT} (should a material system exhibit a breakopen response below the ATPV value).

3.2.4 arc thermal performance value (ATPV), *n*—in arc testing, the incident energy on a material or a multilayer system of materials that results in a 50 % probability that sufficient heat transfer through the tested specimen is predicted to cause the onset of a second-degree skin burn injury based on the Stoll⁹ curve, kW/m²(cal/cm²).

3.2.5 bibs and straps, *n*—as related to electric arc rated protective clothing, a work garment for lower torso coverage that blends trouser functionality with a more open waist. This garment is supported by shoulder straps (straps) with front and/or rear fabric panels (bibs) versus belts on traditional trousers.

3.2.6 breakopen threshold energy (*E*_{BT}), *n*—the incident energy on a material or material system that results in a 50 % probability of breakopen.

3.2.6.1 Discussion—This is the value in J/cm² (cal/cm²) determined by use of logistic regression analysis representing the energy at which breakopen of the layer occurred.

³ AATCC Technical Manual, available from American Association of Textile Chemists and Colorists, PO Box 12215, Research Triangle Park, NC 27709-2215.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org> and International Safety Equipment Association (ISEA), 1901 North Moore Street Suite #808 Arlington, VA 22209-1762, USA, <https://www.safetysystem.org>.

⁵ Available from Canadian Standards Association (CSA), 178 Rexdale Blvd., Toronto, ON M9W 1R3, Canada, <http://www.csagroup.org>.

⁶ Available from Occupational Safety and Health Administration (OSHA), 200 Constitution Ave., NW, Washington, DC 20210, <http://www.osha.gov>.

⁷ Available from International Organization for Standardization (ISO), ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <http://www.iso.org>.

⁸ Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

⁹ Derived from: Stoll, A. M., and Chianta, M. A., “Method and Rating System for Evaluations of Thermal Protection,” *Aerospace Medicine*, Vol 40, 1969, pp. 1232-1238 and Stoll, A. M., and Chianta, M. A., “Heat Transfer through Fabrics as Related to Thermal Injury,” *Transactions—New York Academy of Sciences*, Vol 33, 7, Nov. 1971, pp. 649-670.