



Standard Test Method for Archery Bow Component—Cord Material¹

This standard is issued under the fixed designation F1752; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method establishes the classification and testing of cord as a component material used in the fashioning of bowstrings.

1.2 This test method is not intended to provide information beyond any evaluation of the cord material that would determine its fitness for use other than in the fabrication of completed bowstrings.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D76 Specification for Tensile Testing Machines for Textiles

D123 Terminology Relating to Textiles

D204 Test Methods for Sewing Threads

D1776 Practice for Conditioning and Testing Textiles

D1907 Test Method for Linear Density of Yarn (Yarn Number) by the Skein Method

D2256 Test Method for Tensile Properties of Yarns by the Single-Strand Method

3. Terminology

3.1 *bowstring*, *n*—completed assembly constructed in part from multiple strands of cord material lashed at the center and loop ends with serving string materials and used to connect the limbs of a bow by which to launch an arrow.

3.2 *cord material*, *n*—applied to a variety of natural or manmade textile materials. Cord material may be of monocord, twisted, cable, or braided construction.

¹ This test method is under the jurisdiction of ASTM Committee F08 on Sports Equipment, Playing Surfaces, and Facilities and is the direct responsibility of Subcommittee F08.16 on Archery Products.

Current edition approved Sept. 1, 2014. Published November 2014. Originally approved in 1996. Last previous edition approved in 2010 as F1752 – 96 (2010). DOI: 10.1520/F1752-96R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.3 *denier*, *tex*, *n*—direct yarn numbering systems expressing size of cord material in terms of mass (weight) of unit length per 9000 m (9842 yd) for denier or 1000 m (1094 yd) for tex.

3.4 *diameter*, *n*—measure of the thickness of the cord material.

3.5 *EASL*, *n*—elongation at a set load.

3.6 *elongation*, *n*—amount that a cord material stretches measured as a percentage of the original length either at the point of rupture or at some other interval of applied load.

3.7 *free gage length*, *n*—length of unsupported test specimen between holding clamps and free from contact with any snubbing or other sources that could result in nonuniform gage length measurement.

3.8 *static load stretch/relaxation*, *n*—measure of the amount a cord material moves while under static load and with load subsequently removed, measured as a percentage of the prestressed original length.

3.9 *standard condition*, *n*—condition reached by cord material when in moisture equilibrium with a standard atmosphere of a given temperature and relative humidity.

3.10 *strength*, *n*—maximum force applied to a cord material causing it to break.

4. Significance and Use

4.1 This test method is intended to provide the user of cord materials for bowstrings the basic information for evaluation and procurement.

4.2 This test method is not meant to be all inclusive since special circumstances may occur that will dictate the use of nonconforming procedures for evaluation. Special circumstances and the requirements they establish cannot be anticipated totally and, therefore, must be considered on an individual basis.

5. Test Methods

5.1 *Standard Condition*—Refer to Practice D1776 for standard condition requirements:

$$70 \pm 2^\circ\text{F} \ (21 \pm 1^\circ\text{C}), \ 65 \pm 2\% \text{ relative humidity.} \quad (1)$$

5.2 *Denier, Tex*—Refer to Test Method D1907, Option 1: