



Designation: F1813 – 21

Standard Specification for Wrought Titanium-12Molybdenum-6Zirconium-2Iron Alloy for Surgical Implant (UNS R58120)¹

This standard is issued under the fixed designation F1813; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought titanium-12molybdenum-6zirconium-2iron alloy mill products to be used in the manufacture of surgical implants.²

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E112 Test Methods for Determining Average Grain Size
- E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
- E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
- E1941 Test Method for Determination of Carbon in Refrac-

tory and Reactive Metals and Their Alloys by Combustion Analysis

E2371 Test Method for Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)

E2626 Guide for Spectrometric Analysis of Reactive and Refractory Metals (Withdrawn 2017)⁴

F748 Practice for Selecting Generic Biological Test Methods for Materials and Devices

IEEE/ASTM SI 10 American National Standard for Metric Practice

2.2 Aerospace Materials Specifications:⁵

AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

AMS 2631 Ultrasonic Inspection—Titanium and Titanium Alloy Bar, Billet and Plate

AMS 2380 Approval and Control of Premium-Quality Titanium Alloys

2.3 ISO Standards:⁶

ISO 6982 Metallic Materials Tensile Testing at Ambient Temperature

ISO 9001 Quality Management Standard

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *beta transus, n*—the minimum temperature at which the alpha plus beta phase can transform to 100 % beta phase.

3.1.2 *hot work, n*—any mechanical deformation process performed above the recrystallization temperature.

3.1.3 *lot, n*—the total number of mill products produced from the same melt heat under the same conditions at essentially the same time.

3.1.4 *solution anneal, v*—to heat treat in order to remove precipitates.

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Aug. 15, 2021. Published August 2021. Originally approved in 1997. Last previous edition approved in 2013 as F1813 – 13. DOI: 10.1520/F1813-21.

² FDA 510K application number K903630.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

4. Product Classification

4.1 *Bar*—Rounds, flats, or other shapes from 0.188 in. [4.76 mm] to 4.0 in. [102 mm] in diameter or thickness. (Other sizes and shapes by special order.)

4.2 *Forging Bar*—Bar as described in 4.1 used in the production of forgings. This product may be furnished in the hot worked condition.

4.3 *Wire*—Rounds, flats, or other shapes less than 0.188 in. [4.76 mm] in diameter or thickness.

5. Ordering Information

5.1 Include with inquiries and orders for material under this specification the following information:

- 5.1.1 Quantity,
- 5.1.2 ASTM designation and date of issue,
- 5.1.3 Form (strip, sheet, plate, bar, forging bar, or wire),
- 5.1.4 Condition (see 6.2),
- 5.1.5 Mechanical properties (if applicable for special conditions),
- 5.1.6 Finish (see 6.1),
- 5.1.7 Applicable dimensions including size, thickness, width, length, or drawing number,
- 5.1.8 Special tests (if any), and
- 5.1.9 Other requirements.

6. Materials and Manufacture

6.1 *Finish*—The mill product may be supplied as specified by the purchaser with a descaled or pickled, abrasive blasted, chemically milled, ground, machined, peeled, or polished finish. On billets, bars, plates, and forgings, it is permissible to remove minor surface imperfections by grinding if the resultant area meets the dimensional and surface finish requirements of this specification.

6.2 *Condition*—Material shall be furnished in the solution annealed or hot worked condition.

7. Chemical Requirements

7.1 The heat analysis shall conform to the chemical composition of Table 1. Ingot analysis may be used for reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. The supplier shall not ship material with chemistry outside the requirements specified in Table 1.

TABLE 1 Chemical Requirements

Element	Composition % mass/mass	
	Min	Max
Nitrogen	—	0.05
Carbon	—	0.05
Hydrogen	—	0.020
Iron	1.5	2.5
Oxygen	0.008	0.28
Molybdenum	10.0	13.0
Zirconium	5.0	7.0
Titanium	Balance ^A	

^A The percentage of titanium is determined by difference and need not be determined or certified.

7.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to verify compliance with this specification.

7.2 *Product (Check) Analysis*—The product analysis tolerances shall conform to the product tolerances in Table 2 per AMS 2249. Product analysis tolerances do not broaden the specified heat (ladle or ingot) analysis requirements, but cover variations between laboratories in the measurement of chemical content.

7.2.1 Product (check) analysis limits are not for producer's use at producer's acceptance testing. Product analysis limits are not permitted to be applied to ladle or ingot analysis. The supplier shall not ship material that is outside the limits specified in Table 1.

7.2.2 A product (check) analysis is one performed by the purchaser or supplier of the metal after it has been worked into semi-finished or finished forms or fabricated into parts, and is either for the purpose of verifying the composition of a heat or lot or to determine variations in the composition within the heat. In the analysis of finished parts, these values do not apply to elements whose percentage can be varied by fabrication techniques employed (for example, oxygen, nitrogen, hydrogen) unless the sample is sufficiently large to produce a reliable result, either for the purpose of verifying the composition of a heat or manufacturing lot or to determine variations in the composition within the heat.

7.2.3 Acceptance or rejection of a heat or lot of material may be made by the purchaser on the basis of this product analysis. Product analysis outside the tolerance limits allowed in Table 2 are cause for rejection of the product. A referee analysis may be used if agreed upon by the supplier and purchaser.

7.2.4 For referee purposes, use Test Methods E2371, E1409, E1941, E2626, and E1447 or other analytical methods agreed upon between the purchaser and the supplier.

7.3 Samples for product analysis shall be representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its ability to react with elements such as oxygen, nitrogen, and hydrogen. Therefore, when cutting samples for analysis, the operation should be carried out insofar as possible in a dust-free

TABLE 2 Product Analysis Tolerances^A

Element	Tolerance Under the Minimum or Over the Maximum Limit ^B
Nitrogen	0.02
Carbon	0.002
Hydrogen	0.0002
Iron	0.20
Molybdenum	0.25
Zirconium over 4 to 6 %, inclusive	0.20
Zirconium over 4 to 6 %, inclusive	0.30
Oxygen up to 0.2 %	0.02
Oxygen over to 0.2 %	0.03

^A Refer to AMS 2249.

^B Under the minimum limit not applicable for elements where only a maximum percentage is indicated.