



Standard Specification for Polyethylene of Raised Temperature (PE-RT) Plastic Hot and Cold-Water Tubing and Distribution Systems¹

This standard is issued under the fixed designation F2769; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification establishes requirements for polyethylene of raised temperature (PE-RT) plastic hot- and cold-water tubing and distribution systems components made in one standard dimension ratio and intended for 100 psig (6.9 bar) water service up to and including a maximum working temperature of 180 °F (82 °C). Components are comprised of tubing, fittings, valves and manifolds. Tubing may incorporate an optional polymeric inner, middle or outer layer. Testing of fittings and PE-RT tubing to the requirements of this standard indicate that these fittings are appropriate for use with PE-RT piping systems. Requirements and test methods are included for materials, workmanship, dimensions and tolerances, burst pressure, sustained pressure, oxidative resistance, temperature cycling tests, bend strength and environmental stress cracking. Also included are tests related to system malfunctions. The components covered by this specification are intended for use in residential and commercial, hot and cold, potable water distribution systems, and building supply lines.

1.2 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

NOTE 1—Suggested hydrostatic design stresses and hydrostatic pressure ratings for tubing and fittings are listed in [Appendix X1](#). UV labeling guidelines are provided in [Appendix X2](#). Design, assembly, and installation considerations are provided in [Appendix X3](#). An optional performance qualification and an in-plant quality control program are recommended in [Appendix X4](#).

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification. *This standard does not purport to address all of the safety concerns,*

if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [D618 Practice for Conditioning Plastics for Testing](#)
- [D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure](#)
- [D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings](#)
- [D1600 Terminology for Abbreviated Terms Relating to Plastics \(Withdrawn 2024\)³](#)
- [D1898 Practice for Sampling of Plastics \(Withdrawn 1998\)³](#)
- [D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings](#)
- [D2683 Specification for Socket-Type Polyethylene Fittings for Outside Diameter-Controlled Polyethylene Pipe and Tubing](#)
- [D2749 Symbols for Dimensions of Plastic Pipe Fittings](#)
- [D2837 Test Method for Obtaining Hydrostatic Design Basis for Thermoplastic Pipe Materials or Pressure Design Basis for Thermoplastic Pipe Products](#)
- [D3261 Specification for Butt Heat Fusion Polyethylene \(PE\) Plastic Fittings for Polyethylene \(PE\) Plastic Pipe and Tubing](#)
- [D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials](#)
- [D3895 Test Method for Oxidative-Induction Time of Polyolefins by Differential Scanning Calorimetry](#)

¹ This test method is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.26 on Olefin Based Pipe.

Current edition approved Feb. 1, 2024. Published February 2024. Originally approved in 2009. Last previous edition approved in 2023 as F2769–23a. DOI: 10.1520/F2769-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

- F412** Terminology Relating to Plastic Piping Systems
- F1055** Specification for Electrofusion Type Polyethylene Fittings for Outside Diameter Controlled Polyethylene and Crosslinked Polyethylene (PEX) Pipe and Tubing
- F1282** Specification for Polyethylene/Aluminum/Polyethylene (PE-AL-PE) Composite Pressure Pipe
- F1290** Practice for Electrofusion Joining Polyolefin Pipe and Fittings
- F1473** Test Method for Notch Tensile Test to Measure the Resistance to Slow Crack Growth of Polyethylene Pipes and Resins
- F1960** Specification for Cold Expansion Fittings with PEX Reinforcing Rings for Use with Cross-linked Polyethylene (PEX) and Polyethylene of Raised Temperature (PE-RT) Tubing
- F1807** Specification for Metal Insert Fittings Utilizing a Copper Crimp Ring, or Alternate Stainless Steel Clamps, for SDR9 Cross-linked Polyethylene (PEX) Tubing and SDR9 Polyethylene of Raised Temperature (PE-RT) Tubing
- F2023** Test Method for Evaluating the Oxidative Resistance of Crosslinked Polyethylene (PEX) Pipe, Tubing and Systems to Hot Chlorinated Water
- F2159** Specification for Plastic Insert Fittings Utilizing a Copper Crimp Ring, or Alternate Stainless Steel Clamps for SDR9 Crosslinked Polyethylene (PEX) Tubing and SDR9 Polyethylene of Raised Temperature (PE-RT) Tubing
- F2620** Practice for Heat Fusion Joining of Polyethylene Pipe and Fittings
- F2735** Specification for Plastic Insert Fittings For SDR9 Cross-linked Polyethylene (PEX) and Polyethylene of Raised Temperature (PE-RT) Tubing
- F2080** Specification for Cold-Expansion Fittings with Metal Compression-Sleeves for Crosslinked Polyethylene (PEX) Pipe and SDR9 Polyethylene of Raised Temperature (PE-RT) Pipe
- 2.2 *ANSI Standard:*⁴
- B36.10** Standards Dimensions of Steel Pipe (NTS)
- Z 17.1** Preferred Numbers
- 2.3 *Federal Standard:*⁵
- FED-STD-123** Marking for Shipment (Civil Agencies)
- 2.4 *Military Standard:*⁵
- MIL-STD-129** Marking for Shipment and Storage
- 2.5 *PPI Publications:*⁶
- PPI TR-3** Policies and Procedures for Developing Hydrostatic Design Basis (HDB), Hydrostatic Design Stresses (HDS), Pressure Design Basis (PDB), Strength Design Basis (SDB), and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe
- PPI TR-4** PPI Listing of Hydrostatic Design Basis (HDB), Strength Design Basis (SDB), Pressure Design Basis

(PDB) and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe

2.6 *NSF Standards:*⁷

NSF 14 Standard No. 14 for Plastic Piping Components and Related Materials

NSF 61 Drinking Water System Components – Health Effects

2.7 *ISO Standard:*⁸

ISO 13760 : Plastics pipes for the conveyance of fluids under pressure -- Miner's rule -- Calculation method for cumulative damage

3. Terminology

3.1 Terminology used in this standard is in accordance with Terminologies **F412**, **D1600**, and **D2749** unless otherwise specified. The abbreviation for polyethylene of raised temperature is PE-RT. Plastic tubing denotes a particular diameter schedule of plastic pipe in which outside diameter of the tubing is equal to the nominal size plus 1/8 in. Plastic pipe outside diameter schedule conforms to ANSI B36.10.

3.2 *standard dimension ratio (SDR)*, *n*—a specific ratio of the average specified outside diameter to the minimum specified wall thickness (D_o/t) for outside diameter-controlled plastic pipe, the value of which is derived by adding one to the pertinent number selected from the ANSI Preferred Number Series 10.

F412

3.2.1 *Discussion*—For PE-RT-tubing, it is calculated by dividing the average outside diameter of the tubing in inches or in millimeters by the minimum wall thickness in inches or millimeters. If the wall thickness calculated by this formula is less than 0.070 in. (1.78 mm) it shall be arbitrarily increased to 0.070 in. except for sizes 5/16 in. and smaller. The SDR values shall be rounded to the nearest 0.5

3.3 *Definitions of Terms Specific to This Standard:*

3.3.1 *hydrostatic design stress (HDS)*, *n*—the estimated maximum tensile stress the material is capable of withstanding continuously with a high degree of certainty that failure of the tube will not occur. This stress is circumferential when internal hydrostatic water pressure is applied. For materials with Hydrostatic Strength Classification 3 or 4 per Specification **D3350**, the HDS is equal to the hydrostatic design basis (HDB) times the design factor (DF) for water. For this standard, the design factor is equal to 0.5.

$$HDS = HDB \times DF \\ = HDB \times 0.5 \text{ (for this standard)}$$

3.3.2 *relation between dimensions, hydrostatic design stress, and pressure rating*, *n*—the following expression, commonly known as the ISO equation, is used in this specification to relate dimensions, hydrostatic design stress, and pressure rating:

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ DLA Document Services Building 4/D 700 Robbins Avenue Philadelphia, PA 19111-5094 <http://quicksearch.dla.mil/>

⁶ Available from Plastics Pipe Institute (PPI), 105 Decker Court, Suite 825, Irving, TX 75062, <http://www.plasticpipe.org>.

⁷ Available from NSF International, P.O. Box 130140, 789 N. Dixboro Rd., Ann Arbor, MI 48113-0140, <http://www.nsf.org>.

⁸ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, <http://www.iso.ch>.