



Designation: F3046 – 21

Standard Specification for Wrought Titanium-3Aluminum-2.5Vanadium Alloy for Surgical Implant Applications (UNS R56320)¹

This standard is issued under the fixed designation F3046; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought titanium-3aluminum-2.5vanadium alloy (R56320) to be used in the manufacture of surgical implants.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values of the two systems may result in nonconformance within the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- B367** Specification for Titanium and Titanium Alloy Castings
- E8/E8M** Test Methods for Tension Testing of Metallic Materials
- E29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E290** Test Methods for Bend Testing of Material for Ductility

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Oct. 1, 2021. Published November 2021. Originally approved in 2013. Last previous edition approved in 2013 as F3046 – 13. DOI: 10.1520/F3046-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- E539** Test Method for Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry
- E1409** Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
- E1447** Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
- E1941** Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
- E2371** Test Method for Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)
- E2994** Test Method for Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry (Performance-Based Method)

2.2 ISO Standards:³

- ISO 6892** Metallic Materials Tensile Testing at Ambient Temperature
- ISO 9001** Quality Management Systems—Requirements
- ISO 13485** Medical Devices—Quality Management Systems—Requirements for Regulatory Purposes

2.3 Aerospace Material Specifications:⁴

- AMS 2249** Chemical Check Analysis Limits, Titanium and Titanium Alloys
- AMS 2631** Ultrasonic Inspection—Titanium and Titanium Alloy Bar and Billet

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *beta transus, n*—the minimum temperature at which the alpha-plus-beta phase can transform to 100 % beta phase.

3.1.2 *lot, n*—the total number of mill products produced from one heat under the same conditions at essentially the same time.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

*A Summary of Changes section appears at the end of this standard

4. Product Classification

4.1 *Strip*—Any product under 4.75 mm [0.1875 in.] in thickness and under 610 mm [24 in.] wide.

4.2 *Sheet*—Any product under 4.75 mm [0.1875 in.] in thickness and 610 mm [24 in.] or more in width.

4.3 *Plate*—Any product 4.75 mm [0.1875 in.] thick and over and 250 mm [10 in.] wide and over, with widths greater than five times thickness. Plate up to 101.60 mm [4.00 in.] thick, inclusive, is covered by this specification.

4.4 *Bar*—Round, rectangular, or other complex shaped product delivered straightened and cut to defined lengths.

4.5 *Forging Bar*—Bar as described in 4.4, used for production of forgings, may be furnished in the hot-worked condition.

4.6 *Wire*—Round, rectangular, or other complex shapes of uniform cross section along its entire length furnished in coils or on spools, reels, or other packaging as specified.

4.7 *Other*—Other forms and shapes may be provided by agreement between purchaser and supplier.

5. Ordering Information

5.1 Include with inquiries and orders for material under this specification the following information:

- 5.1.1 Quantity,
- 5.1.2 ASTM designation and date of issue,
- 5.1.3 Form (sheet, strip, plate, bar, forging bar, or wire),
- 5.1.4 Condition (see 6.3),
- 5.1.5 Mechanical properties (if applicable, for special conditions),
- 5.1.6 Finish (see 6.2),
- 5.1.7 Applicable dimensions including size, thickness, width, length, or drawing number,
- 5.1.8 Special tests, if any, and
- 5.1.9 Other requirements.

6. Materials and Manufacture

6.1 The various titanium mill products covered in this specification normally are formed with the conventional forging and rolling equipment found in primary ferrous and nonferrous plants. The alloy is usually multiple melted in arc furnaces (including furnaces such as plasma arc and electron beam) of a type conventionally used for reactive metals.

6.2 *Finish*—The mill product may be furnished to the implant manufacturer as mechanically descaled or pickled, abrasively blasted, chemically milled, ground, machined,

peeled, polished, combinations of these operations, or as specified by the purchaser. On billets, bars, plates, and forgings, it is permissible to remove minor surface imperfections by grinding if the resultant area meets the dimensional and surface finish requirements of this specification.

6.3 *Condition*—Material shall be furnished in the annealed or cold-worked condition. Mechanical properties for conditions other than those listed in Table 1 may be established by agreement between the supplier and the purchaser.

7. Chemical Requirements

7.1 The heat analysis shall conform to the chemical composition specified in Table 2. Ingot analysis may be used for reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. The supplier shall not ship material with chemistry outside the requirements specified in Table 2.

7.1.1 Requirements for the major and minor elemental constituents are listed in Table 2. Also listed are important residual elements. Analysis for elements not listed in Table 2 is not required to verify compliance with this specification.

7.2 Product (Check) Analysis:

7.2.1 Product (check) analysis tolerances shall conform to the product tolerances in Table 3 per AMS 2249 and Specification B367. The product analysis tolerances do not broaden the specified heat (ladle or ingot) analysis requirements but cover variations between laboratories in the measurement of chemical content.

7.2.2 Product (check) analysis limits are not for supplier's/producer's use at supplier's/producer's acceptance testing. Product (check) analysis limits are not permitted to be applied to ladle or ingot analysis. The supplier/producer shall not ship material that is outside the limits specified in Table 1.

7.2.3 A product (check) analysis is one performed by the purchaser or supplier of the metal after it has been worked into semi-finished or finished forms or fabricated into parts, and is either for the purpose of verifying the composition of a heat or manufacturing lot or determining variations in the composition within the heat. In the analysis of finished parts, these values do not apply to elements whose percentage can be varied by fabricating technique employed (for example, oxygen, nitrogen, hydrogen) unless the sample is sufficiently large to produce a reliable result.

7.2.4 Acceptance or rejection of a heat or manufacturing lot of material may be made by the purchaser on the basis of this product (check) analysis. Product (check) analysis outside the

TABLE 1 Annealed Mechanical Properties of Sheet, Strip, Plate, Bar, Wire, and Forgings

Nominal Diameter or Distance Between Parallel Sides, mm [in.]	Tensile Strength min, MPa [psi]	Yield Strength (0.2 % offset) min, MPa [psi]	Elongation ^A in 50 mm [2 in.], min, %	Reduction of Area ^B min, %
Under 4.75 [0.1875] thickness or diameter	620 [90 000]	485 [70 000]	15	...
4.75 [0.1875] to 101.60 [4.00], incl.	620 [90 000]	485 [70 000]	15	25

^A Elongation of material 1.6 mm [0.063 in.] greater width (W) shall be measured using a gauge length of 50.8 mm [2 in.] or 4 W. The gauge length must be reported with the test results. The method for determining elongation of material less than 1.6 mm [0.063 in.] in thickness may be negotiated. Alternatively, a gauge length corresponding to ISO 6892 may be used when agreed upon between supplier and purchaser. (5.65 times the square root of So, where So is the original cross sectional area.) Gauge length shall be reported with the elongation value.

^B Applies to plate only.