



Designation: G114 – 21

Standard Practices for Evaluating the Age Resistance of Polymeric Materials Used in Oxygen Service¹

This standard is issued under the fixed designation G114; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These practices describe procedures that are used to determine the age resistance of plastic, thermosetting, elastomeric, and polymer matrix composite materials exposed to oxygen-containing media.

1.2 While these practices focus on evaluating the age resistance of polymeric materials in oxygen-containing media prior to ignition and combustion testing, they also have relevance for evaluating the age resistance of metals, and nonmetallic oils and greases.

1.3 These practices address both established procedures that have a foundation of experience and new procedures that have yet to be validated. The latter are included to promote research and later elaboration in this practice as methods of the former type.

1.4 The results of these practices may not give exact correlation with service performance since service conditions vary widely and may involve multiple factors such as those listed in 5.8.

1.5 Three procedures are described for evaluating the age resistance of polymeric materials depending on application and information sought.

1.5.1 *Procedure A: Natural Aging*—This procedure is used to simulate the effect(s) of one or more service stressors on a material's oxygen resistance, and is suitable for evaluating materials that experience continuous or intermittent exposure to elevated temperature during service.

1.5.2 *Procedure B: Accelerated Aging Comparative Oxygen Resistance*—This procedure is suitable for evaluating materials that are used in ambient temperature service, or at a temperature that is otherwise lower than the aging temperature, and is useful for developing oxygen compatibility rankings on a laboratory comparison basis.

1.5.3 *Procedure C: Accelerated Aging Lifetime Prediction*—This procedure is used to determine the relationship between

aging temperature and a fixed level of property change, thereby allowing predictions to be made about the effect of prolonged service on oxidative degradation.

1.6 *Units*—The values stated in SI units are to be regarded as the standard; however, all numerical values shall also be cited in the systems in which they were actually measured.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. Specific precautionary statements are given in Section 10.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D395 Test Methods for Rubber Property—Compression Set
- D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D454 Test Method for Rubber Deterioration by Heat and Air Pressure
- D572 Test Method for Rubber—Deterioration by Heat and Oxygen
- D573 Test Method for Rubber—Deterioration in an Air Oven
- D638 Test Method for Tensile Properties of Plastics
- D1349 Practice for Rubber—Standard Conditions for Testing
- D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens
- D2240 Test Method for Rubber Property—Durometer Hardness

¹ These practices are under the jurisdiction of ASTM Committee G04 on Compatibility and Sensitivity of Materials in Oxygen Enriched Atmospheres and are the direct responsibility of Subcommittee G04.02 on Recommended Practices.

Current edition approved Oct. 1, 2021. Published November 2021. Originally approved in 1993. Last previous edition approved in 2014 as G114 – 14. DOI: 10.1520/G0114-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D2512** Test Method for Compatibility of Materials with Liquid Oxygen (Impact Sensitivity Threshold and Pass-Fail Techniques)
- D2863** Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics (Oxygen Index)
- D3039** Test Method for Tensile Properties of Polymer Matrix Composite Materials
- D3045** Practice for Heat Aging of Plastics Without Load
- D4809** Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter (Precision Method)
- G63** Guide for Evaluating Nonmetallic Materials for Oxygen Service
- G72** Test Method for Autogenous Ignition Temperature of Liquids and Solids in a High-Pressure Oxygen-Enriched Environment
- G74** Test Method for Ignition Sensitivity of Nonmetallic Materials and Components by Gaseous Fluid Impact
- G86** Test Method for Determining Ignition Sensitivity of Materials to Mechanical Impact in Ambient Liquid Oxygen and Pressurized Liquid and Gaseous Oxygen Environments
- G94** Guide for Evaluating Metals for Oxygen Service
- G125** Test Method for Measuring Liquid and Solid Material Fire Limits in Gaseous Oxidants
- G126** Terminology Relating to the Compatibility and Sensitivity of Materials in Oxygen Enriched Atmospheres
- 2.2 *CGA Standard*.³
- CGA G-4.3** Commodity Specification for Oxygen
- 2.3 *Military Standards*.⁴
- MIL-PRF-27210** Amendment 1—Oxygen, Aviator's Breathing, Liquid and Gas
- MIL-PRF-25508** Performance Specification: Propellant, Oxygen
- 2.4 *ISO Standards*.⁵
- ISO 2578** Plastics — Determination of time-temperature limits after prolonged exposure to heat
- ISO 9080** Plastics Piping and Ducting Systems — Determination of the Long-term Hydrostatic Strength of Thermoplastics Materials in Pipe Form by Extrapolation

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *aging, n*—see Terminology **G126**.

3.1.2 *accelerated aging, n*—a type of artificial aging whereby the effect of prolonged exposure during service is simulated by aging at elevated temperature.

3.1.3 *artificial aging, n*—see Terminology **G126**.

3.1.4 *oxidative degradation, n*—physical or mechanical property changes occurring as a result of exposure to oxygen-containing media.

3.1.5 *oxygen-containing media, n*—air media containing greater than 21 mole % oxygen, or oxygen-enriched media containing greater than 25 mole % oxygen.

3.1.6 *oxygen resistance, n*—resistance of a material to ignite spontaneously, propagate by sustained combustion, or undergo oxidative degradation.

3.1.7 *oxygen service, n*—applications involving the production, storage, transportation, distribution, or use of oxygen-containing media.

3.1.8 *natural aging, n*—see Terminology **G126**.

3.1.9 *physical aging, n*—aging that occurs during normal storage and which is a function of time after molding or curing.

4. Summary of Practice

4.1 These practices can be used to evaluate systematically the effect of natural aging (Procedure A) or accelerated aging (Procedures B and C) on oxygen resistance. To apply its principle, the user first characterizes the material, then subjects the material to an aging stressor or stressors, followed by re-characterizing the material. Caution must be taken in interpreting results because interactions occurring in service may be different from those simulated during aging.

4.2 It is always more accurate, although not always practical, to determine the effect of natural aging (Procedure A) without resorting to accelerated aging (Procedures B and C). Accelerated aging procedures are more useful for determining material rankings (Procedure B) or for making lifetime predictions (Procedure C).

4.3 In the procedures mentioned, specimens are exposed to a deteriorating influence at a specified elevated temperature at ambient pressure known periods of time. When aging exposures are also conducted at elevated oxygen or air pressure, guidance contained in Test Methods **D572** or **D573**, respectively, must also be followed in addition to the guidance in the standard.

4.4 Summary of Practice for Evaluating the Effect of Aging in Incident Studies:

4.4.1 In incident studies, in which initial characterization data are not available, historical or average property data may be used to draw coarser conclusions about the effect of aging on oxygen resistance.

4.5 Practices for Natural Aging (Procedure A) and Accelerated Aging for Comparative Oxygen Resistance (Procedure B):

4.5.1 The effect of aging is reported as positive or negative depending upon whether the property used to evaluate oxygen resistance increases or decreases, and the magnitude of the effect is reported as the degree to which the measured property changes relative to that of the unaged material.

4.6 Practice for Accelerated Aging for Lifetime Prediction (Procedure C):

³ Available from Compressed Gas Association (CGA), 4221 Walney Rd., 5th Floor, Chantilly, VA 20151-2923, <http://www.cganet.com>.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dsp.dla.mil>.

⁵ Available from International Organization for Standardization (ISO), ISO Central Secretariat, Chemin de Blandinnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <https://www.iso.org>.