

**Aerospace series —
Steel FE-PM1802
(X5CrNiCu15-5) —
Consumable electrode
remelted — Solution
treated and
precipitation treated —
Plate —
6 mm < a ≤ 20 mm —
1 070 MPa ≤ R_m
≤ 1 220 MPa**

The European Standard EN 3479:2007 has the status of a British Standard

ICS 49.025.10

National foreword

This British Standard was published by BSI. It is the UK implementation of EN 3479:2007.

The UK participation in its preparation was entrusted by Technical Committee ACE/61, Metallic materials for aerospace purposes, to Panel ACE/61/-/15, Steels.

A list of organizations represented on ACE/61/-/15 can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2007

© BSI 2007

ISBN 978 0 580 50553 9

Amendments issued since publication

Amd. No.	Date	Comments